Burch



Cove Auric 1009143

Meets or exceeds all ACT® Standards

Crypton Seating Fabric Bleach Cleanable PFAS Free stock may be available



Repeats Not Shown to Scale.

Fabric Specifications

Content88% Polyester 12% NylonFinishCryptonBackingCryptonBleach CleanableYes Ratio: 90% Water / 10% Bleach SolutionWeight19.28 oz. per linear ydWidth54"Ends/PicksEnds: 66 per inch Picks: 81 per inchDirectionalYesRailroadedNo	-		
FinishCryptonBackingCryptonBleach CleanableYes Ratio: 90% Water / 10% Bleach SolutionWeight19.28 oz. per linear ydWidth54"Ends/PicksEnds: 66 per inch Picks: 81 per inchDirectionalYes	Content		
Backing Crypton Bleach Cleanable Yes Ratio: 90% Water / 10% Bleach Solution Weight 19.28 oz. per linear yd Width 54" Ends/Picks Ends: 66 per inch Picks: 81 per inch Directional Yes		12% Nylon	
Bleach Cleanable Yes Ratio: 90% Water / 10% Bleach Solution Weight 19.28 oz. per linear yd Width 54" Ends/Picks Ends: 66 per inch Picks: 81 per inch Directional Yes	Finish	Crypton	
Ratio: 90% Water / 10% Bleach SolutionWeight19.28 oz. per linear ydWidth54"Ends/PicksEnds: 66 per inch Picks: 81 per inchDirectionalYes	Backing	Crypton	
Weight 19.28 oz. per linear yd Width 54" Ends/Picks Ends: 66 per inch Picks: 81 per inch Directional Yes	Bleach Cleanable		
Width 54" Ends/Picks Ends: 66 per inch Picks: 81 per inch Directional Yes		Ratio: 90% Water / 10% Bleach Solution	
Ends/Picks Ends: 66 per inch Picks: 81 per inch Directional Yes	Weight	19.28 oz. per linear yd	
Picks: 81 per inch Directional Yes	Width	54"	
Directional Yes	Ends/Picks	Ends: 66 per inch	
		Picks: 81 per inch	
Railroaded No	Directional	Yes	
	Railroaded	No	

Additional Attributes

PFAS Free	In transition to PFAS Free
	Sku-Dependent
	Contact Customer Care

Recommended Cleaning

Please refer to Detailed Cleaning Instructions.

Performance Characteristics

Abrasion Resistance ASTM D4157	100,000 double rubs*
Brush Pill ASTM D3511	5
Tensile Strength ASTM D5034	Warp: 173.7 lbs. Fill: 153.6 lbs.
Tear Strength ASTM D2262	Warp: 12.5 lbs. Fill: 16.6 lbs.
Seam Slippage ASTM D4034	Warp: 69.4 lbs. Fill: 78.7 lbs.
Colorfastness to Crocking AATCC 8	Dry: 4.5 Wet: 4.5
Colorfastness to Light AATCC 16	Hours: 40.0 Class: 2-3
Flammability**	
CAL TB 117-2013	Passes
NFPA 260	Class 1
UFAC	Class 1

Although we try hard to make sure colors on our site are accurate, actual colors may vary. Please order samples prior to making a purchase.

Final determination of the suitability of this product for an application rests with the user.

* Abrasion test results exceeding ACT Performance Guidelines are not an indicator of product lifespan. Multiple factors affect fabric durability and appearance retention.

** This term and any corresponding data refer to the typical performance in the specific tests indicated and should not be construed to imply the behavior of this or any other material under actual fire conditions.

Toll Free 1.800.841.8111

Visit us at BurchFabrics.com