Burch



Repeats Not Shown to Scale

Cove Cannon 1009147

Meets or exceeds all ACT® Standards

Crypton Seating Fabric Bleach Cleanable PFAS Free stock may be available



*ACT® Registered Certification Marks

Fabric Specifications

| Content | 88% Polyester 12% Nylon |
|------------------|-----------------------------------------------|
| Finish | Crypton |
| Backing | Crypton |
| Bleach Cleanable | Yes Ratio: 90% Water / 10% Bleach Solution |
| Weight | 19.28 oz. per linear yd |
| Width | 54" |
| Ends/Picks | Ends: 66 per inch Picks: 81 per inch |
| Directional | Yes |
| Railroaded | No |

Additional Attributes

| PFAS Free | In transition to PFAS Free Sku-Dependent Contact Customer Care |
|----------------------|----------------------------------------------------------------------|
| Recommended Cleaning | |
| | |

Performance Characteristics

| Abrasion Resistance ASTM D4157 | 100,000 double rubs* | |
|-----------------------------------|--------------------------------------|--|
| Brush Pill ASTM D3511 | 5 | |
| Tensile Strength ASTM D5034 | Warp: 173.7 lbs. Fill: 153.6 lbs. | |
| Tear Strength ASTM D2262 | Warp: 12.5 lbs. Fill: 16.6 lbs. | |
| Seam Slippage ASTM D4034 | Warp: 69.4 lbs. Fill: 78.7 lbs. | |
| Colorfastness to Crocking AATCC 8 | Dry: 4.5 Wet: 4.5 | |
| Colorfastness to Light AATCC 16 | Hours: 40.0 Class: 2-3 | |
| Flammability** | | |
| CAL TB 117-2013 | Passes | |
| NFPA 260 | Class 1 | |
| UFAC | Class 1 | |

Although we try hard to make sure colors on our site are accurate, actual colors may vary. Please order samples prior to making a purchase.

 $\label{product} Final\ determination\ of\ the\ suitability\ of\ this\ product\ for\ an\ application\ rests\ with\ the\ user.$

- * Abrasion test results exceeding ACT Performance Guidelines are not an indicator of product lifespan. Multiple factors affect fabric durability and appearance retention.
- ** This term and any corresponding data refer to the typical performance in the specific tests indicated and should not be construed to imply the behavior of this or any other material under actual fire conditions.

Please refer to Detailed Cleaning Instructions.