Burch



Repeats Not Shown to Scale.

Melody Blaze 1009163

Meets or exceeds all ACT® Standards

Made in the USA Crypton Seating Fabric Bleach Cleanable PFAS Free stock may be available



*ACT® Registered Certification Marks

Fabric Specifications

| Finish Crypton Backing Crypton | 1 10% Water / 10% Bleach Solution |
|----------------------------------|--------------------------------------|
| Backing Crypton | 1 10% Water / 10% Bleach Solution |
| | 10% Water / 10% Bleach Solution |
| | |
| Bleach Cleanable Yes Ratio: 9 | |
| Weight 20.0 oz | . per linear yd |
| Width 54" | |
| Roll Size 50 yard | s |
| | 60 per inch 66 per inch |
| Repeat H - 5.0" V - 10.0 | |
| Directional Yes | |
| Railroaded No | |
| Made in the USA Yes | |

Additional Attributes

| PFAS Free | In transition to PFAS Free Sku-Dependent Contact Customer Care | | |
|---|--|--|--|
| Certifications | | | |
| Greenguard Gold Certified | Yes - Crypton Technology is Greenguard Gold Certified | | |
| Recommended Cleaning | | | |
| Please refer to Detailed Cleaning Instructions. | | | |
| | | | |

Performance Characteristics

| Abrasion Resistance ASTM D4157 | 75,000 double rubs* | |
|-----------------------------------|--------------------------------------|--|
| Brush Pill ASTM D3511 | 3 | |
| Tensile Strength ASTM D5034 | Warp: 184.0 lbs. Fill: 184.0 lbs. | |
| Tear Strength ASTM D2261 | Warp: 21.0 lbs. Fill: 50.0 lbs. | |
| Seam Slippage ASTM D4034 | Warp: 91.0 lbs. Fill: 118.0 lbs. | |
| Colorfastness to Crocking AATCC 8 | Dry: 5.0 Wet: 4.5 | |
| Colorfastness to Light AATCC 16 | Hours: 40.0 Class: 4.0 | |
| Flammability** | | |
| CAL TB 117-2013 | Passes | |
| NFPA 260 | Class 1 | |
| UFAC | Class 1 | |

Although we try hard to make sure colors on our site are accurate, actual colors may vary. Please order samples prior to making a purchase.

 $\label{product} Final\ determination\ of\ the\ suitability\ of\ this\ product\ for\ an\ application\ rests\ with\ the\ user.$

- * Abrasion test results exceeding ACT Performance Guidelines are not an indicator of product lifespan. Multiple factors affect fabric durability and appearance retention.
- ** This term and any corresponding data refer to the typical performance in the specific tests indicated and should not be construed to imply the behavior of this or any other material under actual fire conditions.