250,000 double rubs*

Burch



Repeats Not Shown to Scale

Nexus Silk 1012313

Meets or exceeds all ACT® Standards

High Performance Vinyl Bleach Cleanable FR Free – Compliant with CAL AB 2998



*ACT® Registered Certification Marks

Fabric Specifications

Face	100% Vinyl
Backing	100% Polyester
Finish/Treatment	Resilience™
Bleach Cleanable	Yes Ratio: 90% Water / 10% Bleach Solution
Weight	30.0 oz. per linear yd
Thickness	1.10 mm
Width	54"
Roll Size	30 yards
Directional	Yes
Railroaded	No

Additional Attributes

Prop 65 Compliant	Yes
16P Phthalate Free	Yes
Free of Added FR Chemicals / CAL AB2998 Compliant	Yes
Free of Added Anti-Bacterial Chemicals	Yes
Free of Added Anti-Microbial Chemicals	Yes
BPA Free	Yes
Free of Conflict Minerals	Yes
Formaldehyde Free	Yes
Lead Free	Yes
Sulfide Stain Resistant	Yes
TRIS Free	Yes

Recommended Cleaning

Please refer to Detailed Cleaning Instructions.

Performance Characteristics

Abrasion Resistance ASTM D4157

Tensile Strength cffA-17	Warp: 121.0 lbs. Fill: 125.0 lbs.
Tear Strength CFFA-16b	Warp: 9.8 lbs. Fill: 11.7 lbs.
Seam Slippage CFFA-14	Warp: 44.8 lbs. Fill: 53.7 lbs.
Colorfastness to Crocking AATCC 8	Dry: 5.0 Wet: 5.0
UV Resistance AATCC 16	500 hours
Adhesion cffA-3	Warp: 4.3 lbs. Fill: 4.6 lbs.
Cold Crack CFFA-6	-20° F
Flex cffA-10	25,000 cycles
Flammability**	
CAL TB 117-2013	Passes
NFPA 260	Class 1
UFAC	Class 1
ASTM E-84	Class A or 1
BIFMA CS-191-53, Sec. 3	Passes
IMO 2010 FTP Part 8, 3.1 & 3.2	Passes
FMVSS 302	Passes

Although we try hard to make sure colors on our site are accurate, actual colors may vary. Please order samples prior to making a purchase.

Final determination of the suitability of this product for an application rests with the user.

 $^{{}^{\}star}\, Abrasion \, test \, results \, exceeding \, ACT \, Performance \, Guidelines \, are \, not \, an indicator \, of \, product \, lifespan. \, Multiple \, factors \, affect \, fabric \, durability \, and \, appearance \, retention.$

^{**} This term and any corresponding data refer to the typical performance in the specific tests indicated and should not be construed to imply the behavior of this or any other material under actual fire conditions.