100,000 double rubs\*

Warp: 499.8 lbs.

Fill: 271.2 lbs.

Warp: 10.6 lbs. Fill: 22.6 lbs. Warp: 105.7 lbs.

Fill: 123.9 lbs.

Dry: 4.5 Wet: 4.5

Passes

Class 1

Hours: 40.0

# Burch



Repeats Not Shown to Scale

## Velour Mudslide 1007512

Meets or exceeds all ACT® Standards

Crypton Seating Fabric PFAS Free stock may be available



\*ACT® Registered Certification Marks

Performance Characteristics

Abrasion Resistance ASTM D4157

Brush Pill ASTM D3511

Tensile Strength ASTM D5034

Tear Strength ASTM D2261

Seam Slippage ASTM D4034

Colorfastness to Crocking AATCC 8

Colorfastness to Light AATCC 16

Flammability\*\*

CAL TB 117-2013

NFPA 260

UFAC

### **Fabric Specifications**

Content	100% Polyester
Finish	Crypton
Backing	Crypton
Weight	20.6 oz. per linear yd
Width	54"
Ends/Picks	Ends: 155 per inch Picks: 30 per inch
Directional	Yes
Railroaded	No
Country of Origin	China

### **Additional Attributes**

PFAS Free	In transition to PFAS Free Sku-Dependent Contact Customer Care	
Recommended Cleaning		

Although we try hard to make sure colors on our site are accurate, actual colors may vary. Please order samples prior to making a purchase.

 $Final\ determination\ of\ the\ suitability\ of\ this\ product\ for\ an\ application\ rests\ with\ the\ user.$ 

- \* Abrasion test results exceeding ACT Performance Guidelines are not an indicator of product lifespan. Multiple factors affect fabric durability and appearance retention.
- \*\* This term and any corresponding data refer to the typical performance in the specific tests indicated and should not be construed to imply the behavior of this or any other material under actual fire conditions.

Please refer to Detailed Cleaning Instructions.