



Repeats Not Shown to Scale.

Rivet Red Curry 1008224

Meets or exceeds all ACT® Standards

High Performance Vinyl
Bleach Cleanable
FR Free – Compliant with CAL AB 2998
PFAS Free



*ACT® Registered Certification Marks

Fabric Specifications

| | |
|------------------|---|
| Face | 100% Vinyl |
| Backing | 100% Polyester |
| Finish/Treatment | PRODURATECT™ PLUS |
| Bleach Cleanable | Yes Ratio: 90% Water / 10% Bleach Solution |
| Weight | 25.0 oz. per linear yd |
| Thickness | 1.20 mm |
| Width | 54" |
| Roll Size | 30 yards |
| Directional | Yes |
| Railroaded | No |

Additional Attributes

| | |
|---|-----|
| PFAS Free | Yes |
| 16P Phthalate Free | Yes |
| Free of Added FR Chemicals / CAL AB2998 Compliant | Yes |
| Antibacterial | Yes |
| Antimicrobial | Yes |
| BPA Free | Yes |
| Free of Conflict Minerals | Yes |
| Formaldehyde Free | Yes |
| Free of Heavy Metals | Yes |
| Lead Free | Yes |
| TRIS Free | Yes |
| Low VOC | Yes |

Recommended Cleaning

Please refer to Detailed Cleaning Instructions.

Performance Characteristics

| | |
|--------------------------------|------------------------------------|
| Abrasion Resistance ASTM D4157 | 100,000 double rubs* |
| Tensile Strength ASTM D751 | Warp: 94.0 lbs. Fill: 60.0 lbs. |
| Tear Strength ASTM D751 | Warp: 39.0 lbs. Fill: 25.0 lbs. |
| UV Resistance ASTM G53 (QUV) | 500 hours |
| Adhesion ASTM D751 | Warp: 5.0 lbs. Fill: 5.0 lbs. |
| Cold Crack Fed 191A-5874 | -10° F |

Flammability**

| | |
|--------------------------------|---------|
| CAL TB 117-2013 | Passes |
| NFPA 260 | Class 1 |
| UFAC | Class 1 |
| Federal Aviation Specification | Passes |
| FMVSS 302 | Passes |

Although we try hard to make sure colors on our site are accurate, actual colors may vary. Please order samples prior to making a purchase.

Final determination of the suitability of this product for an application rests with the user.

Proposition 65 Warning: Yes

* Abrasion test results exceeding ACT Performance Guidelines are not an indicator of product lifespan. Multiple factors affect fabric durability and appearance retention.

** This term and any corresponding data refer to the typical performance in the specific tests indicated and should not be construed to imply the behavior of this or any other material under actual fire conditions.

