Burch



Repeats Not Shown to Scale.

Bloom Scarlet 1008406

Meets or exceeds all ACT® Standards

Made in the USA Crypton Seating Fabric Bleach Cleanable



*ACT® Registered Certification Marks

Fabric Specifications

| Content | 44% Post Consumer Recycled Polyester 38% Polyester 18% Post Industrial Recycled Polyester |
|------------------|---|
| Finish | Crypton Green |
| Backing | Crypton Green |
| Bleach Cleanable | Yes Ratio: 90% Water / 10% Bleach Solution |
| Weight | 22.5 oz. per linear yd |
| Width | 54" |
| Roll Size | 50 yards |
| Ends/Picks | Ends: 160 per inch Picks: 76 per inch |
| Repeat | H - 29.25 " V - 25.5 " |
| Directional | Yes |
| Railroaded | No |
| Made in the USA | Yes |

Performance Characteristics

| Brush Pill ASTM D3511 3 | |
|--|------------------------|
| | |
| Tensile Strength ASTM D5034 Warp: 3 Fill: 358 | 866.0 lbs. 8.0 lbs. |
| Tear Strength ASTM D2261 Warp: 5 Fill: 69. | 55.0 lbs. 0 lbs. |
| Seam Slippage ASTM D4034 Warp: 7 Fill: 90. | 74.0 lbs. 0 lbs. |
| Colorfastness to Crocking AATCC 8 Dry: 3.0 Wet: 4. | |
| Colorfastness to Light AATCC 16 Hours: Class: 4 | 1010 |
| Flammability** | |
| CAL TB 117-2013 Passes | ı |
| NFPA 260 Class 1 | |
| UFAC Class 1 | |

Certifications

| Greenguard Gold Certified | Yes - Crypton Technology is Greenguard Gold Certified | |
|------------------------------|--|--|
| | | |

Recommended Cleaning

Please refer to Detailed Cleaning Instructions.

Although we try hard to make sure colors on our site are accurate, actual colors may vary. Please order samples prior to making a purchase.

Final determination of the suitability of this product for an application rests with the user.

 $^{{}^{\}star}\, Abrasion \, test \, results \, exceeding \, ACT \, Performance \, Guidelines \, are \, not \, an indicator \, of \, product \, lifespan. \, Multiple \, factors \, affect \, fabric \, durability \, and \, appearance \, retention.$

^{**} This term and any corresponding data refer to the typical performance in the specific tests indicated and should not be construed to imply the behavior of this or any other material under actual fire conditions.