Burch



Repeats Not Shown to Scale.

Fabric Specifications

Content100% PolyesterFinishCryptonBackingCryptonWeight22.98 oz. per linear ydWidth54"Ends/PicksEnds: 121 per inch Picks: 31 per inchDirectionalYesRailroadedNoCountry of OriginChina		
Backing Crypton Backing Crypton Weight 22.98 oz. per linear yd Width 54" Ends/Picks Ends: 121 per inch Picks: 31 per inch Directional Yes Railroaded No	Content	100% Polyester
Weight 22.98 oz. per linear yd Width 54" Ends/Picks Ends: 121 per inch Picks: 31 per inch Directional Yes Railroaded No	Finish	Crypton
Width 54" Ends/Picks Ends: 121 per inch Picks: 31 per inch Directional Yes Railroaded No	Backing	Crypton
Ends/Picks Ends: 121 per inch Picks: 31 per inch Directional Yes Railroaded No	Weight	22.98 oz. per linear yd
Picks: 31 per inch Directional Yes Railroaded No	Width	54"
Railroaded No	Ends/Picks	•
	Directional	Yes
Country of Origin China	Railroaded	No
	Country of Origin	China

Additional Attributes

PFAS Free	In transition to PFAS Free Sku-Dependent Contact Customer Care	
	contact customer care	

Recommended Cleaning

Please refer to Detailed Cleaning Instructions.

Tagline Muslin 1008744

Meets or exceeds all ACT® Standards

Crypton Seating Fabric PFAS Free stock may be available



*ACT[®] Registered Certification Marks

Performance Characteristics

Abrasion Resistance ASTM D4157	100,000 double rubs*
Brush Pill ASTM D3511	5
Tensile Strength ASTM D5034	Warp: 500.5 lbs. Fill: 324.0 lbs.
Tear Strength ASTM D2262	Warp: 43.3 lbs. Fill: 44.6 lbs.
Seam Slippage ASTM D4034	Warp: 30.6 lbs. Fill: 45.0 lbs.
Colorfastness to Crocking AATCC 8	Dry: 4.5 Wet: 4.5
Colorfastness to Light AATCC 16	Hours: 40.0 Class: 4.0
Flammability**	
CAL TB 117-2013	Passes
NFPA 260	Class 1
UFAC	Class 1

Although we try hard to make sure colors on our site are accurate, actual colors may vary. Please order samples prior to making a purchase.

Final determination of the suitability of this product for an application rests with the user.

* Abrasion test results exceeding ACT Performance Guidelines are not an indicator of product lifespan. Multiple factors affect fabric durability and appearance retention.

** This term and any corresponding data refer to the typical performance in the specific tests indicated and should not be construed to imply the behavior of this or any other material under actual fire conditions.

Toll Free 1.800.841.8111

Visit us at BurchFabrics.com