Burch



Repeats Not Shown to Scale

Suite Patina 1008979

Meets or exceeds all ACT® Standards

Made in the USA Crypton Seating Fabric PFAS Free stock may be available



*ACT® Registered Certification Marks

Fabric Specifications

Content	55% Acrylic 45% Polyester	
Finish	Crypton	
Backing	Crypton	
Weight	18.8 oz. per linear yd	
Width	54"	
Roll Size	55 yards	
Ends/Picks	Ends: 26 per inch Picks: 13.5 per inch	
Directional	Yes	
Railroaded	No	
Country of Origin	USA	

Additional Attributes

Additional Attributes		
PFAS Free	In transition to PFAS Free Sku-Dependent Contact Customer Care	
Certifications		
Greenguard Gold Certified	Yes - Crypton Technology is Greenguard Gold Certified	
Recommended C	leaning	
Please refer to Detail	ed Cleaning Instructions.	

Performance Characteristics

Abrasion Resistance ASTM D4157	50,000 double rubs*
rush Pill astm d3511	4
ensile Strength astm d5034	Warp: 325.0 lbs. Fill: 190.0 lbs.
ear Strength ASTM D2262	Warp: 30.0 lbs. Fill: 45.0 lbs.
eam Slippage ASTM D4034	Warp: 40.0 lbs. Fill: 40.0 lbs.
Colorfastness to Crocking AATCC 8	Dry: 4.0 Wet: 4.0
Colorfastness to Light AATCC 16	Hours: 40.0 Class: 4.0
lammability**	
CAL TB 117-2013	Class 1
IFPA 260	Class 1
IFAC	Class 1
Colorfastness to Crocking AATCC 8 Colorfastness to Light AATCC 16 Flammability** CAL TB 117-2013 IFPA 260	Warp: 40.0 lbs. Fill: 40.0 lbs. Dry: 4.0 Wet: 4.0 Hours: 40.0 Class: 4.0 Class 1 Class 1

Although we try hard to make sure colors on our site are accurate, actual colors may vary. Please order samples prior to making a purchase.

 $Final\ determination\ of\ the\ suitability\ of\ this\ product\ for\ an\ application\ rests\ with\ the\ user.$

- ${\rm *Abrasion\ test\ results\ exceeding\ ACT\ Performance\ Guidelines\ are\ not\ an\ indicator\ of\ product\ lifespan.\ Multiple\ factors\ affect\ fabric\ durability\ and\ appearance\ retention.}$
- ** This term and any corresponding data refer to the typical performance in the specific tests indicated and should not be construed to imply the behavior of this or any other material under actual fire conditions.