# Burch



Repeats Not Shown to Scale

# Charisma Quarry 1010926

Meets or exceeds all ACT® Standards

Made in the USA Sunbrella Contract Seating Fabric Bleach Cleanable Indoor/Outdoor PFAS Free stock may be available



\*ACT® Registered Certification Marks

## **Fabric Specifications**

Content	73% Sunbrella <sup>®</sup> Acrylic 27% Sunbrella <sup>®</sup> Polyester	
Finish	Soil and Stain Repellent	
Backing	Acrylic	
Bleach Cleanable	Yes Ratio: 80% Water / 20% Bleach Solution	
Indoor/Outdoor	Yes	
Weight	19.6 oz. per linear yd	
Width	54"	
Roll Size	50 yards	
Ends/Picks	Ends: 169 per inch Picks: 112 per inch	
Repeat	H - 28.4 " V - 29.1 "	
Directional	Yes	
Railroaded	No	
Country of Origin	USA	

### **Additional Attributes**

Additional Attributes		
PFAS Free	In transition to PFAS Free Sku-Dependent Contact Customer Care	
Certifications		
Greenguard Gold Certified	Yes	
Recommended Cleaning		

#### **Performance Characteristics**

Abrasion Resistance ASTM D4157	97,000 double rubs*
Brush Pill ASTM D3511	5
Tensile Strength ASTM D5034	Warp: 339.0 lbs. Fill: 572.0 lbs.
Tear Strength ASTM D2262	Warp: 39.0 lbs. Fill: 83.0 lbs.
Seam Slippage ASTM D4034	Warp: 102.0 lbs. Fill: 98.0 lbs.
Colorfastness to Crocking AATCC 8	Dry: 5.0 Wet: 5.0
Colorfastness to Light AATCC 16	Hours: 2200 Class: 4.0
Flammability**	
CAL TB 117-2013	Passes
NFPA 260	Class 1
UFAC	Class 1

Although we try hard to make sure colors on our site are accurate, actual colors may vary. Please order samples prior to making a purchase.

 $Final\ determination\ of\ the\ suitability\ of\ this\ product\ for\ an\ application\ rests\ with\ the\ user.$ 

Please refer to Detailed Cleaning Instructions.

<sup>\*</sup> Abrasion test results exceeding ACT Performance Guidelines are not an indicator of product lifespan. Multiple factors affect fabric durability and appearance retention.

<sup>\*\*</sup> This term and any corresponding data refer to the typical performance in the specific tests indicated and should not be construed to imply the behavior of this or any other material under actual fire conditions.