# Burch



Repeats Not Shown to Scale

## Raffia Seaglass 1011345

Meets or exceeds all ACT® Standards

Made in the USA Crypton Seating Fabric Bleach Cleanable PFAS Free stock may be available



\*ACT® Registered Certification Marks

### **Fabric Specifications**

Content	93% Polyester 7% Cotton	
Finish	Crypton	
Backing	Crypton	
Bleach Cleanable	Yes Ratio: 90% Water / 10% Bleach Solution	
Weight	19.8 oz. per linear yd	
Width	54"	
Roll Size	60 yards	
Ends/Picks	Ends: 134 per inch Picks: 36 per inch	
Repeat	H - 22.22 " V - 6.75 "	
Directional	Yes	
Railroaded	No	
Country of Origin	USA	

## **Additional Attributes**

Additional Attribu	Additional Attributes		
PFAS Free	In transition to PFAS Free		
	Sku-Dependent		
	Contact Customer Care		
Certifications			
Greenguard Gold	Yes - Crypton Technology is Greenguard Gold		
Certified	Certified		
Recommended C	leaning		
Please refer to Detail	ed Cleaning Instructions.		

#### **Performance Characteristics**

Abrasion Resistance ASTM D4157	65,000 double rubs*		
Brush Pill ASTM D3511	3		
Tensile Strength ASTM D5034	Warp: 254.2 lbs. Fill: 295.1 lbs.		
Tear Strength ASTM D2262	Warp: 88.1 lbs. Fill: 47.2 lbs.		
Seam Slippage ASTM D4034	Warp: 46.0 lbs. Fill: 26.5 lbs.		
Colorfastness to Crocking AATCC 8	Dry: 4.0 Wet: 3.5		
Colorfastness to Light AATCC 16	Hours: 40.0 Class: 4.0		
Flammability**			
CAL TB 117-2013	Passes		
NFPA 260	Class 1		
UFAC	Class 1		

Although we try hard to make sure colors on our site are accurate, actual colors may vary. Please order samples prior to making a purchase.

 $\label{thm:continuous} Final\ determination\ of\ the\ suitability\ of\ this\ product\ for\ an\ application\ rests\ with\ the\ user.$ 

- \* Abrasion test results exceeding ACT Performance Guidelines are not an indicator of product lifespan. Multiple factors affect fabric durability and appearance retention.
- \*\* This term and any corresponding data refer to the typical performance in the specific tests indicated and should not be construed to imply the behavior of this or any other material under actual fire conditions.