



Repeats Not Shown to Scale.

## Botanica Misty

1011486

Meets or exceeds all ACT® Standards

Made in the USA  
Crypton Seating Fabric  
Bleach Cleanable  
PFAS Free stock may be available



\*ACT® Registered Certification Marks

### Fabric Specifications

Content	100% Polyester
Finish	Crypton
Backing	Crypton
Bleach Cleanable	Yes Ratio: 90% Water / 10% Bleach Solution
Weight	27.0 oz. per linear yd
Width	54"
Roll Size	60 yards
Ends/Picks	Ends: 80 per inch Picks: 102 per inch
Repeat	H - 29.5 " V - 29.25 "
Directional	Yes
Railroaded	No
Country of Origin	USA

### Additional Attributes

PFAS Free	In transition to PFAS Free Sku-Dependent Contact Customer Care
HPD on File	Yes

### Certifications

Greenguard Gold Certified	Yes - Crypton Technology is Greenguard Gold Certified
---------------------------	-------------------------------------------------------

### Recommended Cleaning

Please refer to Detailed Cleaning Instructions.
-------------------------------------------------

### Performance Characteristics

Abrasion Resistance ASTM D4157	51,000 double rubs*
Brush Pill ASTM D3511	5
Tensile Strength ASTM D5034	Warp: 189.0 lbs. Fill: 472.0 lbs.
Tear Strength ASTM D2261-96	Warp: 45.0 lbs. Fill: 64.0 lbs.
Seam Slippage ASTM D4034	Warp: 86.0 lbs. Fill: 108.0 lbs.
Colorfastness to Crocking AATCC 8	Dry: 4.0 Wet: 3.0
Colorfastness to Light AATCC 16	Hours: 40.0 Class: 4.0

### Flammability\*\*

CAL TB 117-2013	Passes
NFPA 260	Class 1
UFAC	Class 1

Although we try hard to make sure colors on our site are accurate, actual colors may vary. Please order samples prior to making a purchase.

Final determination of the suitability of this product for an application rests with the user.

\* Abrasion test results exceeding ACT Performance Guidelines are not an indicator of product lifespan. Multiple factors affect fabric durability and appearance retention.

\*\* This term and any corresponding data refer to the typical performance in the specific tests indicated and should not be construed to imply the behavior of this or any other material under actual fire conditions.