
Burch



Repeats Not Shown to Scale.

Zipline Sapphire 1011649

Meets or exceeds all ACT® Standards

High Performance Vinyl Bleach Cleanable FR Free – Compliant with CAL AB 2998 PFAS Free



*ACT® Registered Certification Marks

Fabric Specifications

| Face | 100% Vinyl |
|-------------------|---|
| Backing | Hi-Loft2™ 100% Polyester |
| Finish/Treatment | Permablok ^{3®} |
| Bleach Cleanable | Yes Ratio: 90% Water / 10% Bleach Solution |
| Weight | 26.0 oz. per linear yd |
| Thickness | .99 mm |
| Width | 54" |
| Roll Size | 30 yards |
| Directional | Yes |
| Railroaded | No |
| Country of Origin | Colombia |

Additional Attributes

| PFAS Free | Yes |
|---|-----|
| Prop 65 Compliant | Yes |
| 16P Phthalate Free | Yes |
| Free of Added FR Chemicals / CAL AB2998 Compliant | Yes |
| BPA Free | Yes |
| Free of Conflict Minerals | Yes |
| Formaldehyde Free | Yes |
| Free of Heavy Metals | Yes |
| Lead Free | Yes |
| Sulfide Stain Resistant | Yes |
| TRIS Free | |

Recommended Cleaning

Please refer to Detailed Cleaning Instructions.

Performance Characteristics

| 100,000 double rubs* | | |
|-------------------------------------|--|--|
| Warp: 121.0 lbs. Fill: 72.0 lbs. | | |
| Warp: 8.7 lbs. Fill: 9.8 lbs. | | |
| Warp: 12.0 lbs. Fill: 8.6 lbs. | | |
| Dry: 4.0 Wet: 4.0 | | |
| 1000 hours | | |
| Warp: 3.3 lbs. Fill: 3.3 lbs. | | |
| -10° F | | |
| 30,000 cycles | | |
| Flammability** | | |
| Passes | | |
| Class 1 | | |
| Class 1 | | |
| | | |

Although we try hard to make sure colors on our site are accurate, actual colors may vary. Please order samples prior to making a purchase.

 $\label{product} Final\ determination\ of\ the\ suitability\ of\ this\ product\ for\ an\ application\ rests\ with\ the\ user.$

- * Abrasion test results exceeding ACT Performance Guidelines are not an indicator of product lifespan. Multiple factors affect fabric durability and appearance retention.
- ** This term and any corresponding data refer to the typical performance in the specific tests indicated and should not be construed to imply the behavior of this or any other material under actual fire conditions.