
# Burch



Repeats Not Shown to Scale

# **Zipline Shadow** 1011662

Meets or exceeds all ACT® Standards

High Performance Vinyl Bleach Cleanable FR Free – Compliant with CAL AB 2998 PFAS Free



\*ACT® Registered Certification Marks

## **Fabric Specifications**

Face	100% Vinyl	
Backing	Hi-Loft2™ 100% Polyester	
Finish/Treatment	Permablok <sup>3®</sup>	
Bleach Cleanable	Yes Ratio: 90% Water / 10% Bleach Solution	
Weight	26.0 oz. per linear yd	
Thickness	.99 mm	
Width	54"	
Roll Size	30 yards	
Directional	Yes	
Railroaded	No	
Country of Origin	Colombia	

#### **Additional Attributes**

PFAS Free	Yes
Prop 65 Compliant	Yes
16P Phthalate Free	Yes
Free of Added FR Chemicals / CAL AB2998 Compliant	Yes
BPA Free	Yes
Free of Conflict Minerals	Yes
Formaldehyde Free	Yes
Free of Heavy Metals	Yes
Lead Free	Yes
Sulfide Stain Resistant	Yes
TRIS Free	Yes

## **Recommended Cleaning**

Please refer to Detailed Cleaning Instructions.

#### **Performance Characteristics**

Abrasion Resistance ASTM D4157	100,000 double rubs*
Tensile Strength CFFA-17	Warp: 121.0 lbs. Fill: 72.0 lbs.
Tear Strength cffA-16	Warp: 8.7 lbs. Fill: 9.8 lbs.
Seam Slippage CFFA-14	Warp: 12.0 lbs. Fill: 8.6 lbs.
Colorfastness to Crocking AATCC 8	Dry: 4.0 Wet: 4.0
UV Resistance CFFA-2	1000 hours
Adhesion CFFA-3	Warp: 3.3 lbs. Fill: 3.3 lbs.
Cold Crack CFFA-6	-10° F
Flex cffA-10	30,000 cycles
Flammability**	
CAL TB 117-2013	Passes
NFPA 260	Class 1
UFAC	Class 1

Although we try hard to make sure colors on our site are accurate, actual colors may vary. Please order samples prior to making a purchase.

 $\label{product} Final\ determination\ of\ the\ suitability\ of\ this\ product\ for\ an\ application\ rests\ with\ the\ user.$ 

- \* Abrasion test results exceeding ACT Performance Guidelines are not an indicator of product lifespan. Multiple factors affect fabric durability and appearance retention.
- \*\* This term and any corresponding data refer to the typical performance in the specific tests indicated and should not be construed to imply the behavior of this or any other material under actual fire conditions.