# Burch



Repeats Not Shown to Scale

# Calypso Sandpiper 1011595

Meets or exceeds all ACT® Standards

Made in the USA Crypton Seating Fabric Bleach Cleanable PFAS Free stock may be available



\*ACT® Registered Certification Marks

## **Fabric Specifications**

Content	56% Polyester 26% Seaqual 17% Post Consumer Recycled Polyester 1% Nylon	
Finish	Crypton	
Backing	Crypton	
Bleach Cleanable	Yes Ratio: 90% Water / 10% Bleach Solution	
Weight	23.2 oz. per linear yd	
Width	54"	
Roll Size	60 yards	
Ends/Picks	Ends: 80 per inch Picks: 16 per inch	
Directional	Yes	
Railroaded	No	
Made in the USA	Yes	

### Additional Attributes

Additional Attributes		
PFAS Free	In transition to PFAS Free Sku-Dependent Contact Customer Care	
Certifications		
Greenguard Gold Certified	Yes - Crypton Technology is Greenguard Gold Certified	
Recommended Cleaning		
Please refer to Details	ed Cleaning Instructions.	

#### **Performance Characteristics**

Abrasion Resistance ASTM D4157	305,000 double rubs*		
Brush Pill ASTM D3511	4		
Tensile Strength ASTM D5034	Warp: 250.0 lbs. Fill: 238.0 lbs.		
Tear Strength ASTM D2261	Warp: 40.0 lbs. Fill: 60.0 lbs.		
Seam Slippage ASTM D4034	Warp: 34.0 lbs. Fill: 33.0 lbs.		
Colorfastness to Crocking AATCC 8	Dry: 4.0 Wet: 3.0		
Colorfastness to Light AATCC 16	Hours: 40.0 Class: 4.0		
Flammability**			
CAL TB 117-2013	Passes		
NFPA 260	Class 1		
UFAC	Class 1		

Although we try hard to make sure colors on our site are accurate, actual colors may vary. Please order samples prior to making a purchase.

Final determination of the suitability of this product for an application rests with the user.

- ${}^{\star}\,\text{Abrasion test results exceeding ACT Performance Guidelines are not an indicator of product lifespan. Multiple factors affect fabric durability and appearance retention.}$
- \*\* This term and any corresponding data refer to the typical performance in the specific tests indicated and should not be construed to imply the behavior of this or any other material under actual fire conditions.