



Repeats Not Shown to Scale.

### Academy Nautical 1012005

Meets or exceeds all ACT<sup>®</sup> Standards

- PVC Free Polyurethane
- Ink Cleanable
- Denim Dye Cleanable
- Bleach Cleanable
- FR Free – Compliant with CAL AB 2998
- PFAS Free



\*ACT<sup>®</sup> Registered Certification Marks

#### Fabric Specifications

Face	100% PVC Free Polyurethane
Backing	100% Polyester
Bleach Cleanable	Yes Ratio: 90% Water / 10% Bleach Solution
Weight	25.4 oz. per linear yd
Thickness	1.40 mm
Width	54"
Roll Size	30 yards
Directional	Yes
Railroaded	No

#### Additional Attributes

Ink Cleanable	Yes
Denim Dye Cleanable	Yes
PFAS Free	Yes
PVC Free	Yes
Prop 65 Compliant	Yes
16P Phthalate Free	Yes
Free of Added FR Chemicals / CAL AB2998 Compliant	Yes
BPA Free	Yes
Free of Conflict Minerals	Yes
Formaldehyde Free	Yes
Free of Heavy Metals	Yes
Lead Free	Yes
Sulfide Stain Resistant	Yes
TRIS Free	Yes
HPD on File	Yes

#### Performance Characteristics

Abrasion Resistance <small>ASTM D4157</small>	250,000 double rubs*
Tensile Strength <small>ASTM D751-06</small>	Warp: 127.0 lbs. Fill: 232.0 lbs.
Tear Strength <small>ASTM D751-06</small>	Warp: 9.3 lbs. Fill: 12.2 lbs.
Seam Slippage <small>ASTM D751-06</small>	Warp: 83.0 lbs. Fill: 80.9 lbs.
Colorfastness to Crocking <small>AATCC 8</small>	Dry: 5.0 Wet: 5.0
UV Resistance <small>AATCC 16</small>	200 hours
Adhesion <small>ASTM D751-06</small>	Warp: 4.6 lbs. Fill: 4.6 lbs.
Blocking <small>CFFA-4</small>	1
Cold Crack <small>CFFA-6</small>	-20° F
Flex <small>ASTM D2097</small>	25,000 cycles
Hydrolysis	10 Weeks

#### Flammability\*\*

CAL TB 117-2013	Passes
NFPA 260	Class 1
UFAC	Class 1

Although we try hard to make sure colors on our site are accurate, actual colors may vary. Please order samples prior to making a purchase.

The use of polyurethane for welt cord in upholstery applications is strongly discouraged. Even though Burch's polyurethane products are designed to exceed industry abrasion standards, when used with welt cord the exposed material becomes more vulnerable to abrasion and may experience premature de-lamination. Burch cannot be held responsible for damage that may occur when used in a welt cord application.

Final determination of the suitability of this product for an application rests with the user.

\* Abrasion test results exceeding ACT Performance Guidelines are not an indicator of product lifespan. Multiple factors affect fabric durability and appearance retention.

\*\* This term and any corresponding data refer to the typical performance in the specific tests indicated and should not be construed to imply the behavior of this or any other material under actual fire conditions.

---

**Recommended Cleaning**

---

Please refer to Detailed Cleaning Instructions.

---

---

Toll Free **1.800.841.8111**

Visit us at **BurchFabrics.com**