Burch



Nexus Chino 1012310

Meets or exceeds all ACT® Standards

High Performance Vinyl Bleach Cleanable FR Free – Compliant with CAL AB 2998 CFFA-HC-201 Compliant



Repeats Not Shown to Scale.

Fabric Specifications

| Face | 100% Vinyl |
|--|---|
| Backing | 100% Polyester |
| Finish/Treatment | Resilience™ |
| Bleach Cleanable | Yes Ratio: 90% Water / 10% Bleach Solution |
| Weight | 30.0 oz. per linear yd |
| Thickness | 1.10 mm |
| Width | 54" |
| Roll Size | 30 yards |
| Directional | Yes |
| Railroaded | No |
| Country of Origin | Taiwan |
| Width Roll Size Directional Railroaded | 54" 30 yards Yes No |

Additional Attributes

| CFFA-HC-201 Compliant | Yes |
|---|-----|
| Prop 65 Compliant | Yes |
| 16P Phthalate Free | Yes |
| Free of Added FR Chemicals / CAL AB2998 Compliant | Yes |
| Free of Added Anti-Bacterial Chemicals | Yes |
| Free of Added Anti-Microbial Chemicals | Yes |
| BPA Free | Yes |
| Free of Conflict Minerals | Yes |
| Formaldehyde Free | Yes |
| Lead Free | Yes |
| Sulfide Stain Resistant | Yes |
| TRIS Free | Yes |
| Performanded Cleaning | |

Recommended Cleaning

Performance Characteristics

| Abrasion Resistance ASTM D4157 | 250,000 double rubs* | | |
|-----------------------------------|--------------------------------------|--|--|
| Tensile Strength CFFA-17 | Warp: 121.0 lbs. Fill: 125.0 lbs. | | |
| Tear Strength CFFA-16b | Warp: 9.8 lbs. Fill: 11.7 lbs. | | |
| Seam Slippage CFFA-14 | Warp: 44.8 lbs. Fill: 53.7 lbs. | | |
| Colorfastness to Crocking AATCC 8 | Dry: 5.0 Wet: 5.0 | | |
| UV Resistance AATCC 16 | 500 hours | | |
| Adhesion CFFA-3 | Warp: 4.3 lbs. Fill: 4.6 lbs. | | |
| Cold Crack CFFA-6 | -20° F | | |
| Flex CFFA-10 | 25,000 cycles | | |
| Flammability** | | | |
| CAL TB 117-2013 | Passes | | |
| NFPA 260 | Class 1 | | |
| UFAC | Class 1 | | |
| ASTM E-84 | Class A or 1 | | |
| BIFMA CS-191-53, Sec. 3 | Passes | | |
| IMO 2010 FTP Part 8, 3.1 & 3.2 | Passes | | |
| FMVSS 302 | Passes | | |

Although we try hard to make sure colors on our site are accurate, actual colors may vary. Please order samples prior to making a purchase.

Final determination of the suitability of this product for an application rests with the user.

* Abrasion test results exceeding ACT Performance Guidelines are not an indicator of product lifespan. Multiple factors affect fabric durability and appearance retention.

** This term and any corresponding data refer to the typical performance in the specific tests indicated and should not be construed to imply the behavior of this or any other material under actual fire conditions. Toll Free 1.800.841.8111

Visit us at BurchFabrics.com