Burch



Palomino Nickel 1012718

Meets or exceeds all ACT[®] Standards

High Performance Vinyl Bleach Cleanable FR Free – Compliant with CAL AB 2998 PFAS Free



*ACT[®] Registered Certification Marks

Repeats Not Shown to Scale.

Fabric Specifications

| Face | 100% Vinyl | |
|-------------------|---|--|
| Backing | 100% Polyester | |
| Finish/Treatment | Resilience™ | |
| Bleach Cleanable | Yes Ratio: 90% Water / 10% Bleach Solution | |
| Weight | 32.0 oz. per linear yd | |
| Thickness | 1.30 mm | |
| Width | 54" | |
| Roll Size | 30 yards | |
| Directional | Yes | |
| Railroaded | No | |
| Country of Origin | Turkey | |
| | | |

Additional Attributes

| PFAS Free | Yes |
|---|-----|
| Prop 65 Compliant | Yes |
| 16P Phthalate Free | Yes |
| Free of Added FR Chemicals / CAL AB2998 Compliant | Yes |
| Antibacterial | Yes |
| Antimicrobial | Yes |
| BPA Free | Yes |
| Free of Conflict Minerals | Yes |
| Formaldehyde Free | Yes |
| Free of Heavy Metals | Yes |
| Lead Free | Yes |
| Sulfide Stain Resistant | Yes |
| TRIS Free | Yes |

Performance Characteristics

| Abrasion Resistance ASTM D4157 | 250,000 double rubs* |
|-----------------------------------|--------------------------------------|
| Tensile Strength ASTM D751-06 | Warp: 175.0 lbs. Fill: 163.0 lbs. |
| Tear Strength ASTM D2261 | Warp: 11.2 lbs. Fill: 18.9 lbs. |
| Seam Slippage ASTM D751 | Warp: 60.7 lbs. Fill: 79.1 lbs. |
| Colorfastness to Crocking AATCC 8 | Dry: 5.0 Wet: 5.0 |
| UV Resistance AATCC 16 | 300 hours |
| Adhesion ASTM D751-06 | Warp: 7.4 lbs. Fill: 6.1 lbs. |
| Cold Crack CFFA-6 | -20° F |
| Flex ASTM D2097 | 25,000 cycles |
| Flammability** | |
| CAL TB 117-2013 | Passes |
| NFPA 260 | Class 1 |
| | |

Although we try hard to make sure colors on our site are accurate, actual colors may vary. Please order samples prior to making a purchase.

Final determination of the suitability of this product for an application rests with the user.

* Abrasion test results exceeding ACT Performance Guidelines are not an indicator of product lifespan. Multiple factors affect fabric durability and appearance retention.

** This term and any corresponding data refer to the typical performance in the specific tests indicated and should not be construed to imply the behavior of this or any other material under actual fire conditions. **Recommended Cleaning**

Please refer to Detailed Cleaning Instructions.

Toll Free 1.800.841.8111

Visit us at BurchFabrics.com