# Burch



Repeats Not Shown to Scale

## **Jackpot Cypress** 1012771

Meets or exceeds all ACT® Standards

High Performance Vinyl Bleach Cleanable FR Free – Compliant with CAL AB 2998 PFAS Free



\*ACT® Registered Certification Marks

### **Fabric Specifications**

Face	100% Vinyl
Backing	100% Polyester
Bleach Cleanable	Yes Ratio: 90% Water / 10% Bleach Solution
Weight	30.0 oz. per linear yd
Thickness	0.80 mm
Width	54"
Roll Size	30 yards
Directional	No
Railroaded	No

#### **Additional Attributes**

PFAS Free	Yes
Prop 65 Compliant	Yes
16P Phthalate Free	Yes
Free of Added FR Chemicals / CAL AB2998 Compliant	Yes
Antibacterial	Yes
Antimicrobial	Yes
BPA Free	Yes
Free of Conflict Minerals	Yes
Formaldehyde Free	Yes
Free of Heavy Metals	Yes
Lead Free	Yes
Sulfide Stain Resistant	Yes
TRIS Free	Yes

#### **Recommended Cleaning**

Please refer to Detailed Cleaning Instructions.

#### **Performance Characteristics**

Abrasion Resistance ASTM D4157	100,000 double rubs*
Tensile Strength ASTM D751	Warp: 79.1 lbs. Fill: 70.5 lbs.
Tear Strength ASTM D2261-07	Warp: 4.2 lbs. Fill: 8.3 lbs.
Seam Slippage ASTM D751-06	Warp: 46.3 lbs. Fill: 32.6 lbs.
Colorfastness to Crocking AATCC 8	Dry: 2.5 Wet: 5.0
UV Resistance AATCC 16-3	200 hours
Adhesion	Warp: 6.9 lbs. Fill: 5.0 lbs.
Cold Crack cffA-6	-10° F
Flex ASTM D2097	25,000 cycles
Flammability**	
CAL TB 117-2013	Passes
NFPA 260	Class 1

Although we try hard to make sure colors on our site are accurate, actual colors may vary. Please order samples prior to making a purchase.

 $\label{thm:condition} Final \ determination \ of \ the \ suitability \ of \ this \ product \ for \ an \ application \ rests \ with \ the \ user.$ 

<sup>\*</sup> Abrasion test results exceeding ACT Performance Guidelines are not an indicator of product lifespan. Multiple factors affect fabric durability and appearance retention.

<sup>\*\*</sup> This term and any corresponding data refer to the typical performance in the specific tests indicated and should not be construed to imply the behavior of this or any other material under actual fire conditions.