



Repeats Not Shown to Scale.

Solace Tendril 1012692

Meets or exceeds all ACT® Standards

- PVC Free Polyurethane
- Ink Cleanable
- Denim Dye Cleanable
- Bleach Cleanable
- FR Free – Compliant with CAL AB 2998
- PFAS Free



*ACT® Registered Certification Marks

Fabric Specifications

Face	95% Polyurethane 5% Silicone
Backing	100% Polyester
Bleach Cleanable	Yes Ratio: 90% Water / 10% Bleach Solution
Weight	19.0 oz. per linear yd
Thickness	1.20 mm
Width	54"
Roll Size	30 yards
Directional	Yes
Railroaded	No
Country of Origin	Taiwan

Additional Attributes

Ink Cleanable	Yes
Denim Dye Cleanable	Yes
PFAS Free	Yes
PVC Free	Yes
Prop 65 Compliant	Yes
Free of Added FR Chemicals / CAL AB2998 Compliant	Yes
Antibacterial	Yes
Antimicrobial	Yes
BPA Free	Yes
Free of Conflict Minerals	Yes
Formaldehyde Free	Yes
Free of Heavy Metals	Yes
Lead Free	Yes
Mildew Resistant	Yes

Performance Characteristics

Abrasion Resistance ASTM D4157	250,000 double rubs*
Tensile Strength ASTM D751-06	Warp: 175.0 lbs. Fill: 163.0 lbs.
Tear Strength ASTM D751-06	Warp: 10.1 lbs. Fill: 12.6 lbs.
Seam Slippage ASTM D751-06	Warp: 69.9 lbs. Fill: 67.7 lbs.
Colorfastness to Crocking AATCC 8	Dry: 5.0 Wet: 5.0
UV Resistance AATCC 16	200 hours
Adhesion ASTM D751-06	Warp: 11.4 lbs. Fill: 7.5 lbs.
Blocking CFFA-4	1
Cold Crack CFFA-6	-20° F
Flex ASTM D2097-03	25,000 cycles
Hydrolysis	15 Weeks

Flammability**

CAL TB 117-2013	Passes
NFPA 260	Class 1

Although we try hard to make sure colors on our site are accurate, actual colors may vary. Please order samples prior to making a purchase.

The use of polyurethane for welt cord in upholstery applications is strongly discouraged. Even though Burch's polyurethane products are designed to exceed industry abrasion standards, when used with welt cord the exposed material becomes more vulnerable to abrasion and may experience premature de-lamination. Burch cannot be held responsible for damage that may occur when used in a welt cord application.

Final determination of the suitability of this product for an application rests with the user.

* Abrasion test results exceeding ACT Performance Guidelines are not an indicator of product lifespan. Multiple factors affect fabric durability and appearance retention.

** This term and any corresponding data refer to the typical performance in the specific tests indicated and should not be construed to imply the behavior of this or any other material under actual fire conditions.

Sulfide Stain Resistant	Yes
TRIS Free	Yes
Low VOC	Yes
Recommended Cleaning	
Please refer to Detailed Cleaning Instructions.	

Toll Free **1.800.841.8111**

Visit us at **BurchFabrics.com**