



Repeats Not Shown to Scale.

BADLANDS OXBLOOD

1013070

Meets or exceeds all ACT® Standards

High Performance Vinyl
 Bleach Cleanable
 FR Free – Compliant with CAL AB 2998
 PFAS Free



*ACT® Registered Certification Marks

Fabric Specifications

| | |
|-------------------|---|
| Face | 100% Hyphyn™ Biodegradable Vinyl |
| Backing | 100% Hyphyn™ Biodegradable Polyester |
| Finish/Treatment | Hyphyn |
| Bleach Cleanable | Yes Ratio: 90% Water / 10% Bleach Solution |
| Weight | 31.0 oz. per linear yd |
| Thickness | 1.20 mm |
| Width | 54" |
| Roll Size | 30 yards |
| Directional | Yes |
| Railroaded | No |
| Country of Origin | Taiwan |

Additional Attributes

| | |
|---|-----|
| PFAS Free | Yes |
| Prop 65 Compliant | Yes |
| 16P Phthalate Free | Yes |
| Free of Added FR Chemicals / CAL AB2998 Compliant | Yes |
| Antibacterial | Yes |
| Antimicrobial | Yes |
| BPA Free | Yes |
| Free of Conflict Minerals | Yes |
| Formaldehyde Free | Yes |
| Free of Heavy Metals | Yes |
| Lead Free | Yes |
| Sulfide Stain Resistant | Yes |
| TRIS Free | Yes |
| Low VOC | Yes |

Performance Characteristics

| | |
|-----------------------------------|------------------------------------|
| Abrasion Resistance ASTM D4157-13 | 250,000 double rubs* |
| Tensile Strength ASTM D751-06 | Warp: 88.5 lbs. Fill: 71.5 lbs. |
| Tear Strength ASTM D751-06 | Warp: 9.6 lbs. Fill: 12.6 lbs. |
| Seam Slippage ASTM D751-06 | Warp: 46.8 lbs. Fill: 45.4 lbs. |
| Colorfastness to Crocking AATCC 8 | Dry: 5.0 Wet: 5.0 |
| UV Resistance | 200 hours |
| Adhesion ASTM D751-06 | Warp: 4.1 lbs. Fill: 5.0 lbs. |
| Cold Crack CFFA-6 | -20° F |
| Flex ASTM D2097 | 25,000 cycles |

Flammability**

| | |
|-----------------|---------|
| CAL TB 117-2013 | Passes |
| NFPA 260 | Class 1 |
| FMVSS 302 | Passes |

Although we try hard to make sure colors on our site are accurate, actual colors may vary. Please order samples prior to making a purchase.

Hyphyn™ Vinyl biodegrades over 90% within 24 months in landfill conditions, per ASTM D5511 testing. Its patented enzyme system activates only in anaerobic environments.

Final determination of the suitability of this product for an application rests with the user.

* Abrasion test results exceeding ACT Performance Guidelines are not an indicator of product lifespan. Multiple factors affect fabric durability and appearance retention.

** This term and any corresponding data refer to the typical performance in the specific tests indicated and should not be construed to imply the behavior of this or any other material under actual fire conditions.

| | |
|-------------|-----|
| HPD on File | Yes |
|-------------|-----|

Recommended Cleaning

Please refer to Detailed Cleaning Instructions.

Toll Free **1.800.841.8111**

Visit us at **BurchFabrics.com**