Burch



Repeats Not Shown to Scale

Neutra Wooden 1001976

Meets or exceeds all ACT® Standards

PFAS Free



*ACT® Registered Certification Marks

Fabric Specifications

Content	100% Recycled Polyester		
Backing	None		
Weight	8.73 oz. per linear yd		
Width	66"		
Roll Size	60 yards		
Ends/Picks	Ends: 145 per inch Picks: 30 per inch		
Repeat	H - 6.7 " V - 8.1 "		
Directional	Yes		
Railroaded	No		

Performance Characteristics

Tensile Strength ASTM D5034	Warp: 100.0 lbs. Fill: 61.0 lbs.		
Tear Strength ASTM D2262	Warp: 23.0 lbs. Fill: 22.0 lbs.		
Colorfastness to Crocking AATCC 8	Dry: 4.0 Wet: 3.0		
Colorfastness to Light AATCC 16A	Hours: 40.0 Class: 4.0		
Flammability**			
CAL TB 117-E	Passes		
ASTM E-84	Class A or 1		

Additional Attributes

PFAS Free	Yes
-----------	-----

Recommended Cleaning**

S - Clean this fabric with pure solvents (petroleum distillate-based products, Energine, Carbona, Renuzit, or similar products may be used), in a well-ventilated room. Cleaning by a professional furniture cleaning service only is recommended.

Although we try hard to make sure colors on our site are accurate, actual colors may vary. Please order samples prior to making a purchase.

 $\label{thm:continuous} Final\ determination\ of\ the\ suitability\ of\ this\ product\ for\ an\ application\ rests\ with\ the\ user.$

- ** This term and any corresponding data refer to the typical performance in the specific tests indicated and should not be construed to imply the behavior of this or any other material under actual fire conditions.
- ** Cleaning information is offered for general guidance and is not a guarantee. The use of certain cleaning agents can be harmful to the surface appearance and lifespan of a product. Burch Fabrics assumes no responsibility for damage to a product resulting from lack of cleaning, improper cleaning or the misuse of cleaning agents. Certain clothing and accessory dyes (such as those used on denim jeans) may migrate to materials and cause permanent damage. Burch Fabrics cannot be held responsible for dye transfer caused by external contaminants.