



Repeats Not Shown to Scale.

### Prodigy Equestrian 1006618

Meets or exceeds all ACT® Standards

High Performance Vinyl

Indoor/Outdoor  
PFAS Free



\*ACT® Registered Certification Marks

#### Fabric Specifications

Face	100% Vinyl
Backing	100% Polyester
Finish/Treatment	Stain Resistant Finish
Indoor/Outdoor	Yes
Weight	30.75 oz. per linear yd
Thickness	1.22 mm
Width	54"
Roll Size	40 yards
Directional	No
Railroaded	No

#### Additional Attributes

PFAS Free	Yes
16P Phthalate Free	Yes
Antibacterial	Yes
Antimicrobial	Yes
BPA Free	Yes
Free of Conflict Minerals	Yes
Formaldehyde Free	Yes
Free of Heavy Metals	Yes
Lead Free	Yes
Mildew Resistant	Yes
Sulfide Stain Resistant	Yes
TRIS Free	Yes
Low VOC	Yes

#### Recommended Cleaning

Please refer to Detailed Cleaning Instructions.

#### Performance Characteristics

Abrasion Resistance <small>ASTM D4157</small>	100,000 double rubs*
Tensile Strength <small>CFFA-17</small>	Warp: 110.0 lbs. Fill: 75.0 lbs.
Tear Strength <small>Fed Std 191A-5134</small>	Warp: 8.0 lbs. Fill: 10.0 lbs.
Colorfastness to Crocking <small>AATCC 8</small>	Dry: 4.0-5.0 Wet: 4.0-5.0
UV Resistance <small>CFFA-2</small>	1000 hours
Adhesion <small>CFFA-3</small>	Warp: 3.5 lbs. Fill: 3.5 lbs.
Blocking <small>CFFA-4</small>	2
Cold Crack <small>CFFA-6</small>	-25° F
Flex <small>ASTM D2097-03</small>	30,000 cycles

#### Flammability\*\*

CAL TB 117-2013	Passes
NFPA 260	Class 1
UFAC	Class 1
FMVSS 302	Passes

Although we try hard to make sure colors on our site are accurate, actual colors may vary. Please order samples prior to making a purchase.

Final determination of the suitability of this product for an application rests with the user.

Proposition 65 Warning: Yes

\* Abrasion test results exceeding ACT Performance Guidelines are not an indicator of product lifespan. Multiple factors affect fabric durability and appearance retention.

\*\* This term and any corresponding data refer to the typical performance in the specific tests indicated and should not be construed to imply the behavior of this or any other material under actual fire conditions.

