



Repeats Not Shown to Scale.

Spirit Millennium Ivory

US

500

Meets or exceeds all ACT® Standards

High Performance Vinyl  
Bleach Cleanable  
PFAS Free



\*ACT® Registered Certification Marks

Fabric Specifications

Face	100% Vinyl
Backing	100% Polyester
Finish/Treatment	Advanced BeautyGard® Oil Resistant
Bleach Cleanable	Yes Ratio: 90% Water / 10% Bleach Solution
Weight	37.0 oz. per linear yd
Thickness	1.28 mm
Width	54"
Roll Size	30 yards
Directional	No
Railroaded	No
Country of Origin	USA

Additional Attributes

PFAS Free	Yes
Antibacterial	Yes
Antimicrobial	Yes
Mildew Resistant	Yes
Sulfide Stain Resistant	Yes

Recommended Cleaning

Please refer to Detailed Cleaning Instructions.

Performance Characteristics

Abrasion Resistance <small>ASTM D4157</small>	1,500,000 double rubs*
Tensile Strength <small>Fed Std 191A-5100</small>	Warp: 65.0 lbs. Fill: 60.0 lbs.
Tear Strength <small>Fed Std 191A-5136</small>	Warp: 14.0 lbs. Fill: 12.0 lbs.
Seam Slippage <small>CS-273-65</small>	Warp: 25.0 lbs. Fill: 20.0 lbs.
Colorfastness to Crocking <small>Fed Std 191A-5651</small>	Dry: Good Wet: Good
UV Resistance <small>SAE J1885</small>	226 hours
Adhesion <small>CS-273-65</small>	Warp: 3.0 lbs. Fill: 3.0 lbs.
Blocking <small>191A-5872</small>	3
Cold Crack <small>191A-5874</small>	-20° F
Flex <small>CS-273-65</small>	15,000 cycles

Flammability\*\*

CAL TB 117-2013	Passes
NFPA 260	Class 1
UFAC	Class 1
Federal Aviation Specification	Passes
Federal Specification	Passes
FMVSS 302	Passes

Although we try hard to make sure colors on our site are accurate, actual colors may vary. Please order samples prior to making a purchase.

Final determination of the suitability of this product for an application rests with the user.

Proposition 65 Warning: Yes

\* Abrasion test results exceeding ACT Performance Guidelines are not an indicator of product lifespan. Multiple factors affect fabric durability and appearance retention.

\*\* This term and any corresponding data refer to the typical performance in the specific tests indicated and should not be construed to imply the behavior of this or any other material under actual fire conditions.

