



Repeats Not Shown to Scale.

## Nexus Curry 1008595

Meets or exceeds all ACT® Standards

High Performance Vinyl  
Bleach Cleanable  
FR Free – Compliant with CAL AB 2998  
PFAS Free



\*ACT® Registered Certification Marks

### Fabric Specifications

Face	100% Vinyl
Backing	100% Polyester
Finish/Treatment	Resilience™
Bleach Cleanable	Yes Ratio: 90% Water / 10% Bleach Solution
Weight	30.0 oz. per linear yd
Thickness	1.10 mm
Width	54"
Roll Size	30 yards
Directional	Yes
Railroaded	No

### Additional Attributes

PFAS Free	Yes
Prop 65 Compliant	Yes
16P Phthalate Free	Yes
Free of Added FR Chemicals / CAL AB2998 Compliant	Yes
Free of Added Anti-Bacterial Chemicals	Yes
Free of Added Anti-Microbial Chemicals	Yes
BPA Free	Yes
Free of Conflict Minerals	Yes
Formaldehyde Free	Yes
Lead Free	Yes
Sulfide Stain Resistant	Yes
TRIS Free	Yes

### Recommended Cleaning

Please refer to Detailed Cleaning Instructions.

### Performance Characteristics

Abrasion Resistance ASTM D4157	250,000 double rubs*
Tensile Strength CFFA-17	Warp: 121.0 lbs. Fill: 125.0 lbs.
Tear Strength CFFA-16b	Warp: 9.8 lbs. Fill: 11.7 lbs.
Seam Slippage CFFA-14	Warp: 44.8 lbs. Fill: 53.7 lbs.
Colorfastness to Crocking AATCC 8	Dry: 5.0 Wet: 5.0
UV Resistance AATCC 16	500 hours
Adhesion CFFA-3	Warp: 4.3 lbs. Fill: 4.6 lbs.
Cold Crack CFFA-6	-20° F
Flex CFFA-10	25,000 cycles

### Flammability\*\*

CAL TB 117-2013	Passes
NFPA 260	Class 1
UFAC	Class 1
ASTM E-84	Class A or 1
BIFMA CS-191-53, Sec. 3	Passes
IMO 2010 FTP Part 8, 3.1 & 3.2	Passes
FMVSS 302	Passes

Although we try hard to make sure colors on our site are accurate, actual colors may vary. Please order samples prior to making a purchase.

Final determination of the suitability of this product for an application rests with the user.

\* Abrasion test results exceeding ACT Performance Guidelines are not an indicator of product lifespan. Multiple factors affect fabric durability and appearance retention.

\*\* This term and any corresponding data refer to the typical performance in the specific tests indicated and should not be construed to imply the behavior of this or any other material under actual fire conditions.

