Burch

Technical Details



Repeats Not Shown to Scale.

# Gilded Depth 1009868

Meets or exceeds all ACT® Standards

High Performance Vinyl
Ink Cleanable
Denim Dye Cleanable
Bleach Cleanable
FR Free – Compliant with CAL AB 2998
PFAS Free

*

*ACT® Registered Certification Marks

## Fabric Specifications

| | |
|---|---|
| Face | 100% Vinyl |
| Backing | 100% Polyester |
| Finish/Treatment | Forbid SRT™ |
| Bleach Cleanable | Yes<br>Ratio: 90% Water / 10% Bleach Solution |
| Weight | 30.0 oz. per linear yd |
| Thickness | 1.00 mm |
| Width | 54" |
| Roll Size | 30 yards |
| Directional | Yes |
| Railroaded | No |

## Additional Attributes

| | |
|---|---|
| Ink Cleanable | Yes |
| Denim Dye Cleanable | Yes |
| PFAS Free | Yes |
| Forbid SRT | Yes |
| Free of Added FR Chemicals / CAL AB2998 Compliant | Yes |
| Antibacterial | Yes |
| Antimicrobial | Yes |
| BPA Free | Yes |
| Free of Conflict Minerals | Yes |
| Formaldehyde Free | Yes |
| Lead Free | Yes |
| Mildew Resistant | Yes |
| Sulfide Stain Resistant | Yes |
| TRIS Free | Yes |

## Performance Characteristics

| | |
|---|---|
| Abrasion Resistance Wyzenbeek | 100,000 double rubs* |
| Tensile Strength ASTM D751 | Warp: 120.0 lbs.<br>Fill: 70.0 lbs. |
| Tear Strength ASTM D751 | Warp: 7.0 lbs.<br>Fill: 7.0 lbs. |
| Colorfastness to Crocking CFFA-7 | Dry: 4.0<br>Wet: 4.0 |
| UV Resistance ASTM G154 | 300 hours |
| Adhesion CFFA-3A | Warp: 4.5 lbs.<br>Fill: 4.5 lbs. |
| Blocking CFFA-4 | 4 |
| Cold Crack CFFA-6 | -10° F |

## Flammability**

| | |
|---|---|
| CAL TB 117-2013 | Passes |
| NFPA 260 | Passes |
| UFAC | Passes |
| BIFMA CS-191-53, Sec. 3 | Passes |
| BIFMA Upholstery, Sec. 4 | Passes |
| FMVSS 302 | Passes |

Although we try hard to make sure colors on our site are accurate, actual colors may vary. Please order samples prior to making a purchase.

Final determination of the suitability of this product for an application rests with the user.

Proposition 65 Warning: Yes

* Abrasion test results exceeding ACT Performance Guidelines are not an indicator of product lifespan. Multiple factors affect fabric durability and appearance retention.

** This term and any corresponding data refer to the typical performance in the specific tests indicated and should not be construed to imply the behavior of this or any other material under actual fire conditions.

| Recommended Cleaning |
| --- |
| Please refer to Detailed Cleaning Instructions. |