



Repeats Not Shown to Scale.

Beacon Fireside 1010784

Meets or exceeds all ACT® Standards

Made in the USA  
Sunbrella Contract Seating Fabric  
Bleach Cleanable  
Indoor/Outdoor  
PFAS Free stock may be available



\*ACT® Registered Certification Marks

Fabric Specifications

Content	100% Sunbrella® Acrylic
Finish	Soil and Stain Repellent
Backing	Acrylic
Bleach Cleanable	Yes Ratio: 80% Water / 20% Bleach Solution
Indoor/Outdoor	Yes
Weight	12.6 oz. per linear yd
Width	54"
Roll Size	55 yards
Ends/Picks	Ends: 42 per inch Picks: 55 per inch
Directional	Yes
Railroaded	No
Made in the USA	Yes

Additional Attributes

PFAS Free	In transition to PFAS Free Sku-Dependent Contact Customer Care
-----------	----------------------------------------------------------------------

Certifications

Greenguard Gold Certified	Yes
---------------------------	-----

Recommended Cleaning

Please refer to Detailed Cleaning Instructions.
-------------------------------------------------

Performance Characteristics

Abrasion Resistance ASTM D4157	70,000 double rubs*
Brush Pill ASTM D3511	5
Tensile Strength ASTM D5034	Warp: 206.7 lbs. Fill: 248.3 lbs.
Tear Strength ASTM D2261	Warp: 15.9 lbs. Fill: 17.9 lbs.
Seam Slippage ASTM D4034	Warp: 73.8 lbs. Fill: 76.5 lbs.
Colorfastness to Crocking AATCC 8	Dry: 5.0 Wet: 5.0
Colorfastness to Light AATCC 16	Hours: 1500 Class: 3.0

Flammability\*\*

CAL TB 117-2013	Passes
NFPA 260	Class 1
UFAC	Class 1

Although we try hard to make sure colors on our site are accurate, actual colors may vary. Please order samples prior to making a purchase.

Final determination of the suitability of this product for an application rests with the user.

\* Abrasion test results exceeding ACT Performance Guidelines are not an indicator of product lifespan. Multiple factors affect fabric durability and appearance retention.

\*\* This term and any corresponding data refer to the typical performance in the specific tests indicated and should not be construed to imply the behavior of this or any other material under actual fire conditions.