



Repeats Not Shown to Scale.

Traction Greystone / 7758

Meets or exceeds all ACT® Standards

Vertical Surface Fabric



*ACT® Registered Certification Marks

Fabric Specifications

Content	100% Polyester
Backing	Lightly Backed
Weight	11.7 oz. per linear yd
Thickness	0.00 mm
Width	66"
Ends/Picks	Ends: 0 per inch Picks: 0 per inch
Directional	Yes
Railroaded	No

Recommended Cleaning**

WS - Water-based cleaning agents and foam may be used for cleaning. This fabric may also be cleaned with mild, water-free solvents. Cleaning by a professional cleaning service is recommended.

Performance Characteristics

Abrasion Resistance	0 double rubs
Tensile Strength ASTM D5034	Warp: 281.0 lbs. Fill: 181.0 lbs.
Tear Strength ASTM D2262	Warp: 29.7 lbs. Fill: 31.4 lbs.
Colorfastness to Crocking AATCC 8	Dry: 5.0 Wet: 5.0
Colorfastness to Light AATCC 16A	Hours: 40.0 Class: 5.0

Flammability**

CAL TB 117-E	Passes
ASTM E-84	Class A or 1

Although we try hard to make sure colors on our site are accurate, actual colors may vary. Please order samples prior to making a purchase.

Final determination of the suitability of this product for an application rests with the user.

** This term and any corresponding data refer to the typical performance in the specific tests indicated and should not be construed to imply the behavior of this or any other material under actual fire conditions.

** Cleaning information is offered for general guidance and is not a guarantee. The use of certain cleaning agents can be harmful to the surface appearance and lifespan of a product. Burch Fabrics assumes no responsibility for damage to a product resulting from lack of cleaning, improper cleaning or the misuse of cleaning agents. Certain clothing and accessory dyes (such as those used on denim jeans) may migrate to materials and cause permanent damage. Burch Fabrics cannot be held responsible for dye transfer caused by external contaminants.

Although we try hard to make sure colors on our site are accurate, actual colors may vary. Please order samples prior to making a purchase.
Final determination of the suitability of this product for an application rests with the user.

Visit us at BurchFabrics.com