Burch



Repeats Not Shown to Scale

Chamea II Navy CY 17

Meets or exceeds all ACT® Standards

High Performance Vinyl Bleach Cleanable PFAS Free



*ACT® Registered Certification Marks

Fabric Specifications

| Face | 100% Vinyl |
|------------------|---|
| Backing | 100% Polyester |
| Finish/Treatment | Advanced BeautyGard® |
| Bleach Cleanable | Yes Ratio: 90% Water / 10% Bleach Solution |
| Weight | 26.0 oz. per linear yd |
| Width | 54" |
| Roll Size | 35 yards |
| Directional | No |
| Railroaded | No |

Additional Attributes

| PFAS Free | Yes |
|-------------------------|-----|
| Antibacterial | Yes |
| Antimicrobial | Yes |
| Mildew Resistant | Yes |
| Sulfide Stain Resistant | Yes |
| Recommended Cleaning | |

Performance Characteristics

| Abrasion Resistance ASTM D4157 | 250,000 double rubs* |
|----------------------------------|----------------------|
| Tensile Strength CFFA-17 | Warp: 85.0 lbs. |
| | Fill: 60.0 lbs. |
| Tear Strength cffA-16 | Warp: 12.0 lbs. |
| | Fill: 12.0 lbs. |
| Seam Slippage CFFA-14 | Warp: 50.0 lbs. |
| | Fill: 25.0 lbs. |
| Colorfastness to Crocking CFFA-7 | Dry: Good |
| | Wet: Good |
| UV Resistance SAE J1885 | 226 hours |
| Adhesion CFFA-3 | Warp: 3.5 lbs. |
| | Fill: 3.5 lbs. |
| Blocking cffA-4 | 3 |
| Cold Crack CFFA-6 | -20° F |
| Flammability** | |
| CAL TB 117-2013 | Passes |
| NFPA 260 | Class 1 |
| UFAC | Class 1 |
| FMVSS 302 | Passes |
| | |

Although we try hard to make sure colors on our site are accurate, actual colors may vary. Please order samples prior to making a purchase.

Final determination of the suitability of this product for an application rests with the user.

Proposition 65 Warning: Yes

Please refer to Detailed Cleaning Instructions.

^{*} Abrasion test results exceeding ACT Performance Guidelines are not an indicator of product lifespan. Multiple factors affect fabric durability and appearance retention.

^{**} This term and any corresponding data refer to the typical performance in the specific tests indicated and should not be construed to imply the behavior of this or any other material under actual fire conditions.