

DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

March 6, 2017

BURCH FABRICS
4200 Brockton Drive SE
Grand Rapids, MI 49512

Reference: Flammability Test Report
Lab Identification No. 24091
Invoice No. 55260

To Whom it May Concern:

One (1) fabric sample, identified as **BADGE**, was received and tested in accordance with the California Technical Bulletin 117-2013, Section 1, Cover Fabric Test. The results are as follows:

Test Results

Char

9mm

9mm

10mm

The sample submitted **meets** the requirements of the above standard. There were no ignitions or smoldering after 45 minutes on any of the three specimens tested. In addition, none of the three test specimens displayed a char which was greater than 45 mm.


If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSDmr





DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

"We Test Per Your Request" →

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

December 18, 2015



Reference: Laboratory Test Report
Lab Identification No. 17952
Invoice No. 48782 (Attached)

Dear Ms. Houser:

One (1) fabric sample, identified as **BADGE** was received and tested in accordance with the NFPA 260, "Cigarette Ignition Resistance of Components of Upholstered Furniture, 2009 Edition", (Cover Fabric Test). The results are as follows:

<u>Test Results</u>		
<u>Vertical Char Lengths</u>		
10mm	8mm	10mm


The fabric sample submitted meets the requirements of the above standard and may be considered a Class I Cover Fabric. There were no ignitions on any of the three specimens tested. In addition, none of the three test specimens displayed a vertical char which was equal to or greater than 45 mm.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Bobby E. Puett

BEP/mr
Attachment



DIVERSIFIED TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

December 18, 2015



Reference: Laboratory Test Report
Lab Identification No. 17952
Invoice No. 48782 (Attached)

Dear Ms. Houser:

One (1) fabric sample, identified as **BADGE** was received and tested in accordance with the UPHOLSTERED FURNITURE ACTION COUNCIL Fabric Classification Test Method--1990. The results are as follows:

Test Results
Vertical Char Lengths

10mm 8mm 10mm

Class

I

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Bobby E. Puett

BEP/mr
Attachment