

ISO: 9001 Certified

TB Cal. 117-2013 Quality Assurance Lab Test Report

Test Date:

08/23/2023

Material #:

Material Name:

Ballad

Customer ID:

Ballad Crypton

Reference Material:

Contents:

52.99% POLY(UV), 47.01% OLEFIN

Wgt oz/Linear yd:

13.68

Section 1: Cover Fabric Test

Length of Char in Inches

Specimen #1

0.500 Inch

Specimen #2

0.438 Inch

Specimen #3

0.500 Inch

Char Length:

Pass

If the char measures 1.8 inches or less, the result is passing. If the char measures more than 1.8 inches, the result is failing.

45 Minute Smolder

Resistance:

Pass

QA Lab Manager:

Barbara Grant

Date:

08/29/2023

Telephone #: 828-893-4382



ISO: 9001 Certified

NFPA 260 Certificate Quality Assurance Lab Test Report

Test Date:

08/23/2023

Material #:

Material Name:

Ballad

Customer ID:

Ballad Crypton

Reference Material:

Contents:

52.99% POLY(UV), 47.01% OLEFIN

Wgt oz/Linear yd:

13.68

Section 1: Cover Fabric Test

Length of Char in Inches

Specimen #1 0.500 Inch
Specimen #2 0.438 Inch
Specimen #3 0.500 Inch
Char Length: Class I

If the char measures 1.75 inches or less, passing results are categorizeed as Class I. If the char measures more than 1.75 inches, the result is failing, Failing results are categorized as Class II

QA Lab Manager:

Barbara Grant

Date:

08/29/2023

Telephone #:

828-893-4382



ISO: 9001 Certified

UFAC Quality Assurance Lab Test Report

Test Date:

08/23/2023

Material #:

Material Name:

Ballad

Customer ID:

Ballad Crypton

Reference Material:

Contents:

52.99% POLY(UV), 47.01% OLEFIN

Wgt oz/Linear yd:

13.68

Section 1: Cover Fabric Test

Length of Char in Inches

Specimen #1

0.500 Inch

Specimen #2

0.438 Inch

Specimen #3

0.500 Inch

Char Length:

Class I

If the char measures 1.75 inches or less, passing results are categorizeed as Class I. If the char measures more than 1.75 inches, the result is failing, Failing results are categorized as Class II

QA Lab Manager:

Barbara Grant

Date:

08/29/2023

Telephone #:

828-893-4382