



Date of Issue: 4/15/2021 Report Number: 21-000887

Revision Number:2

Date Order Received: 03/18/2021

For the Account of:

Burch 4800 Brockton Dr SE Grand Rapids, MI 49512

Client's Identification:	Billiard			

CERTIFICATE OF TESTING

TEST PERFORMED: California Technical Bulletin 117: June 2013 - Requirements, Test Procedure and Apparatus for Testing the Smolder Resistance of Materials Used in Upholstered Furniture - Cover Fabric Test

TEST RESULTS

	Specimen	Char Length (in)	Extinguished in 45 Minutes
Initial Test	1	0.7	Υ
	2	0.6	Y
	3	0.7	Υ

NOTES

Test Conditions:

70 ±5°F, 50 ±5% Relative Humidity

ACCEPTANCE CRITERIA

A material is considered to pass or fail based on the following criteria:

- 1. A single mock-up test specimen fails to meet the requirements of this test procedure if any of the following criteria occurs:
 - The mock-up test specimen continues to smolder after the 45 minute test duration
 - A vertical char length of more than 1.8 inches (45mm) develops on the cover fabric
 - The mock-up test specimen transitions to open flaming
- The cover fabric passes the test if three initial mock-up specimens pass the test, i.e. the cigarettes burn their full length and are no longer smoldering
- If more than one initial specimen fails, the cover fabric fails the test
- If any one of the three initial specimens fails, repeat the test on additional three specimens

5.		three additional specimens pass the test, the cover fabric passes the test. If any one of the additional three specimens the cover fabric fails the test
CONCLUSION	ı	Based on the above Results and Acceptance Criteria, the item tested is: ☑ Pass ☐ Fail

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures as specified by the standard stated above.	nd equipment
A thin short Signature	Date Order Completed: 03/2
Authorized Signature	





Date of Issue: 4/15/2021 Report Number: 21-000887

Revision Number:2

Date Order Received: 03/18/2021

For the Account of:

Burch

4200 Brockton Dr SE Grand Rapids, MI 49512

Client's Identification:

Billiard

CERTIFICATE OF TESTING

TEST PERFORMED: NFPA 260 Standard Methods of Tests and Classification System for Cigarette Ignition Resistance of Components of Upholstered Furniture – 2013; Fabric Cover Test and UFAC Fabric Classification Test Method – 1990; Standard Test Methods for Cigarette Ignition Resistance of Components of Upholstered Furniture ASTM E 1353-16 – Cover Fabric Test

TEST RESULTS

Specimen	Char Length (in)
1	0.6
2	0.6
3	0.6

NOTES

Test Conditions: 70 ±4°F, 65 ±5% Relative Humidity

ACCEPTANCE CRITERIA

- 1. If the test specimen has no ignition, or if no individual specimen yields a vertical char of 45 mm (1.75 in; ASTM states 1.8 in.) or less, the fabric is classified a Class I cover fabric.
- 2. If the vertical char of the test specimen greater than 45 mm (1.75 in.; ASTM states 1.8 in), the fabric is classified a Class II cover fabric
- fabric.

 3. If an obvious ignition of the polyurethane substrate occurs on the test assembly, the fabric is classified a Class II cover fabric

3. If an obv	ous ignition of the polyurethane substrate occurs on the test assembly, the labric is classified a Class II cover labric.
CONCLUSION	Based on the above Results and Acceptance Criteria, the item tested is: ☑ Class I ☐ Class II
specified by the sta	
Authorized Signature	Date Order Completed: 03/29/2021