

Burch

TB Cal. 117-2013 **Quality Assurance Lab Test Report**

Test Date: 02/17/2025
Material #:
Material Name:
Customer ID: Blazer Crypton
Reference Material:
Contents: 38.81% OLEFIN, 38.81% POLY, 22.38% POLY (UV)
Wgt oz/Linear yd: 18.4

Section 1: Cover Fabric Test

Length of Char in Inches

Specimen #1 0.500 Inch
Specimen #2 0.563 Inch
Specimen #3 0.563 Inch
Char Length: Pass

If the char measures 1.8 inches or less, the result is passing.
If the char measures more than 1.8 inches, the result is failing.

45 Minute Smolder
Resistance: Pass

VP Product Assurance:	Jennifer Gwynn
Date:	02/18/2025
Telephone #:	828-874-2181

Burch

NFPA 260 Certificate Quality Assurance Lab Test Report

Test Date: 02/17/2025
Material #:
Material Name:
Customer ID: Blazer Crypton
Reference Material:
Contents: 38.81% OLEFIN, 38.81% POLY, 22.38% POLY(UV)
Wgt oz/Linear yd: 18.4

Section 1: Cover Fabric Test

	Length of Char in Inches
Specimen #1	0.500 Inch
Specimen #2	0.563 Inch
Specimen #3	0.563 Inch
Char Length:	Class I

If the char measures 1.75 inches or less, passing results are categorized as Class I. If the char measures more than 1.75 inches, the result is failing, Failing results are categorized as Class II

VP Product Assurance:	Jennifer Gwynn
Date:	02/18/2025
Telephone #:	828-874-2181

Burch

UFAC **Quality Assurance Lab Test Report**

Test Date: 02/17/2025
Material #:
Material Name:
Customer ID: Blazer Crypton
Reference Material:
Contents: 38.81% OLEFIN, 38.81% POLY, 22.38% POLY (UV)
Wgt oz/Linear yd: 18.4

Section 1: Cover Fabric Test

	Length of Char in Inches
Specimen #1	0.500 Inch
Specimen #2	0.563 Inch
Specimen #3	0.563 Inch
Char Length:	Class I

If the char measures 1.75 inches or less, passing results are categorized as Class I. If the char measures more than 1.75 inches, the result is failing, Failing results are categorized as Class II

VP Product Assurance:	Jennifer Gwynn
Date:	02/18/2025
Telephone #:	828-874-2181