

Burch

TB Cal. 117-2013

Quality Assurance Lab Test Report

Test Date: 05/30/2025

Material Name: Borderline

Customer ID: Borderline Panel

Reference Material:

Contents: 100.00% PCRPOLY

Wgt oz/Linear yd: 9.84

Section 1: Cover Fabric Test

Length of Char in Inches

Specimen #1 0.500 Inch

Specimen #2 0.563 Inch

Specimen #3 0.563 Inch

Char Length: **Pass**

If the char measures 1.8 inches or less, the result is passing.
If the char measures more than 1.8 inches, the result is failing.

45 Minute Smolder Resistance: **Pass**

-----| VP Product Assurance: Jennifer Gwynn |-----

-----| Date: 07/24/2025 |-----

-----| Telephone #: 828-874-2181 |-----

Burch

NFPA 260 Certificate Quality Assurance Lab Test Report

Test Date: 05/30/2025

Material Name: Borderline

Customer ID: Borderline Panel

Reference Material:

Contents: 100.00% PCRPOLY

Wgt oz/Linear yd: 9.84

Section 1: Cover Fabric Test

Length of Char in Inches

Specimen #1 0.500 Inch

Specimen #2 0.563 Inch

Specimen #3 0.563 Inch

Char Length: **Class I**

If the char measures 1.75 inches or less, passing results are categorized as Class I. If the char measures more than 1.75 inches, the result is failing. Failing results are categorized as Class II

VP Product Assurance: Jennifer Gwynn

Date: 07/24/2025

Telephone #: 828-874-2181

Burch

UFAC

Quality Assurance Lab Test Report

Test Date: 05/30/2025

Material Name: Borderline

Customer ID: Borderline Panel

Reference Material:

Contents: 100.00% PCRPOLY

Wgt oz/Linear yd: 9.84

Section 1: Cover Fabric Test

Length of Char in Inches

Specimen #1 0.500 Inch

Specimen #2 0.563 Inch

Specimen #3 0.563 Inch

Char Length: **Class I**

If the char measures 1.75 inches or less, passing results are categorized as Class I. If the char measures more than 1.75 inches, the result is failing, Failing results are categorized as Class II

-----| VP Product Assurance: Jennifer Gwynn |-----

Date: 07/24/2025

Telephone #: 828-874-2181