

# Burch

ISO: 9001 Certified

## ***TB Cal. 117-2013 Quality Assurance Lab Test Report***

Test Date: 09/09/2022  
Material #:  
Material Name:  
Customer ID: Canopy Crypton  
Reference Material:  
Contents: 59.82% PCRPOLY, 40.18% POLY  
Wgt oz/Linear yd: 14.688

### ***Section 1: Cover Fabric Test***

---

	Length of Char in Inches
Specimen #1	0.438 Inch
Specimen #2	0.500 Inch
Specimen #3	0.438 Inch
Char Length:	Pass

If the char measures 1.8 inches or less, the result is passing.  
If the char measures more than 1.8 inches, the result is failing.

45 Minute Smolder  
Resistance: Pass

QA Lab Manager:	Barbara Grant
Date:	09/30/2022
Telephone #:	828-893-4382

# Burch

ISO: 9001 Certified

## ***NFPA 260 Certificate Quality Assurance Lab Test Report***

**Test Date:** 09/09/2022  
**Material #:**  
**Material Name:**  
**Customer ID:** Canopy Crypton  
**Reference Material:**  
**Contents:** 59.82% PCRPOLY, 40.18% POLY  
**Wgt oz/Linear yd:** 14.688

### ***Section 1: Cover Fabric Test***

---

	Length of Char in Inches
<b>Specimen #1</b>	<b>0.438 Inch</b>
<b>Specimen #2</b>	<b>0.500 Inch</b>
<b>Specimen #3</b>	<b>0.438 Inch</b>
<b>Char Length:</b>	<b>Class I</b>

If the char measures 1.75 inches or less, passing results are categorized as Class I. If the char measures more than 1.75 inches, the result is failing, Failing results are categorized as Class II

<b>QA Lab Manager:</b>	<b>Barbara Grant</b>
<b>Date:</b>	<b>09/30/2022</b>
<b>Telephone #:</b>	<b>828-893-4382</b>

# Burch

ISO: 9001 Certified

## UFAC

### Quality Assurance Lab Test Report

Test Date: 09/09/2022  
Material #:  
Material Name:  
Customer ID: Canopy Crypton  
Reference Material:  
Contents: 59.82% PCRPOLY, 40.18% POLY  
Wgt oz/Linear yd: 14.688

#### Section 1: Cover Fabric Test

---

	Length of Char in Inches
Specimen #1	0.438 Inch
Specimen #2	0.500 Inch
Specimen #3	0.438 Inch
Char Length:	Class I

If the char measures 1.75 inches or less, passing results are categorized as Class I. If the char measures more than 1.75 inches, the result is failing, Failing results are categorized as Class II

QA Lab Manager:	Barbara Grant
Date:	09/30/2022
Telephone #:	828-893-4382