

DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

July 24, 2017

Burch
4200 Brockton Dr SE
Grand Rapids, MI 49512

Reference: Flammability Test Report
Lab Identification No. 26220
Invoice No. 57334

Dear Burch:

One (1) fabric sample, identified **CHRONICLE CRYPTON**, was received and tested in accordance with the NFPA 260, "Cigarette Ignition Resistance of Components of Upholstered Furniture, 2013 Edition", (Cover Fabric Test). The results are as follows:

Test Results

Vertical Char Lengths

10mm 10mm 12mm

The sample submitted **meets** the requirements of the above standard and may be considered a **Class I Cover Fabric**. There were no ignitions on any of the three specimens tested. In addition, none of the three test specimens displayed a vertical char which was equal to or greater than 45 mm.


If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr





DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

July 24, 2017

Burch
4200 Brockton Dr SE
Grand Rapids, MI 49512

Reference: Flammability Test Report
Lab Identification No. 26220
Invoice No. 57334

Dear Burch:

One (1) fabric sample, identified **CHRONICLE CRYPTON**, was received and tested in accordance with the **UPHOLSTERED FURNITURE ACTION COUNCIL Fabric Classification Test Method--1990**. The results are as follows:

<u>Test Results</u>		
<u>Vertical Char Lengths</u>		
10mm	10mm	12mm
<u>Class</u>		
	I	


If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr





DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

July 24, 2017

Burch
4200 Brockton Dr SE
Grand Rapids, MI 49512

Reference: Flammability Test Report
Lab Identification No. 26220
Invoice No. 57334

Dear Burch:

One (1) fabric sample, identified **CHRONICLE CRYPTON**, was received and tested in accordance with the California Technical Bulletin 117-2013, Section 1, Cover Fabric Test. The results are as follows:

Test Results

Char

11mm

10mm

10mm

The sample submitted **meets** the requirements of the above standard. There were no ignitions or smoldering after 45 minutes on any of the three specimens tested. In addition, none of the three test specimens displayed a char which was greater than 45 mm.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr

