

**DIVERSIFIED**  
**TESTING LABORATORIES, INC.**  
WORLDWIDE SERVICE

336 WEST FRONT STREET  
P.O. BOX 4004  
BURLINGTON, NORTH CAROLINA 27215  
PHONE (336) 227-7710 • FAX (336) 227-1175  
[www.diversifiedtestinglabs.com](http://www.diversifiedtestinglabs.com)

"We Test Per Your Request"

February 10, 2017

Burch  
4200 Brockton Dr SE  
Grand Rapids, MI 49512

Reference: Flammability Test Report  
Lab Identification No. 23699  
Invoice No. 54845

Dear Burch:

One (1) fabric sample, identified **COTTAGE CRYPTON**, was received and tested in accordance with the California Technical Bulletin 117-2013, Section 1, Cover Fabric Test. The results are as follows:

Test Results

Char

10mm

9mm

9mm

The sample submitted **meets** the requirements of the above standard. There were no ignitions or smoldering after 45 minutes on any of the three specimens tested. In addition, none of the three test specimens displayed a char which was greater than 45 mm.


If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr





**DIVERSIFIED**  
TESTING LABORATORIES, INC.  
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET  
P.O. BOX 4004  
BURLINGTON, NORTH CAROLINA 27215  
PHONE (336) 227-7710 • FAX (336) 227-1175  
www.diversifiedtestinglabs.com

October 4, 2016

Burch  
4200 Brockton Dr SE  
Grand Rapids, MI 49512

Reference: Flammability Test Report  
Lab Identification No. 21934  
Invoice No. 53071

Dear Burch:

One (1) fabric sample, identified **COTTAGE** was received and tested in accordance with the NFPA 260, "Cigarette Ignition Resistance of Components of Upholstered Furniture, 2013 Edition", (Cover Fabric Test). The results are as follows:

Test Results

Vertical Char Lengths

9mm      13mm      12mm

The sample submitted **meets** the requirements of the above standard and may be considered a **Class I Cover Fabric**. There were no ignitions on any of the three specimens tested. In addition, none of the three test specimens displayed a vertical char which was equal to or greater than 45 mm.


If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr





**DIVERSIFIED**  
TESTING LABORATORIES, INC.  
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET  
P.O. BOX 4004  
BURLINGTON, NORTH CAROLINA 27215  
PHONE (336) 227-7710 • FAX (336) 227-1175  
www.diversifiedtestinglabs.com

October 4, 2016

Burch  
4200 Brockton Dr SE  
Grand Rapids, MI 49512

Reference: Flammability Test Report  
Lab Identification No. 21934  
Invoice No. 53071

Dear Burch:

One (1) fabric sample, identified **COTTAGE**, was received and tested in accordance with the UPHOLSTERED FURNITURE ACTION COUNCIL Fabric Classification Test Method--1990. The results are as follows:

Test Results

Vertical Char Lengths

9mm      13mm      12mm

Class

I

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr

