

DIVERSIFIED

TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

"We Test Per Your Request"

May 21, 2014

Burch Fabrics
4200 Brockton Dr SE
Grand Rapids, MI 49512

Reference: Laboratory Test Report
Lab Identification No. 10422
Invoice No. 41178 (Attached)

Dear Ms. Houser:

One (1) fabric sample, identified as **COVE- CRYPTON**, was received and tested in accordance with the California Technical Bulletin 117-2013, Section 1, Cover Fabric Test. The results are as follows:

Test Results - Char

15mm	16mm	13mm
------	------	------


The sample submitted **meets** the requirements of the above standard. There were no ignitions or smoldering after 45 minutes on any of the three specimens tested. In addition, none of the three test specimens displayed a char which was greater than 45 mm.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Bobby E. Puett

BEP/mr
Attachment



DIVERSIFIED

TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

May 21, 2014

Burch Fabrics
4200 Brockton Dr SE
Grand Rapids, MI 49512

Reference: Laboratory Test Report
Lab Identification No. 10422
Invoice No. 41178 (Attached)

Dear Ms. Houser:

One (1) fabric sample, identified as **COVE- CRYPTON** was received and tested in accordance with the NFPA 260, "Cigarette Ignition Resistance of Components of Upholstered Furniture, 2009 Edition", (Cover Fabric Test). The results are as follows:

Test Results
Vertical Char Lengths

16mm 14mm 14mm


The fabric sample submitted **meets** the requirements of the above standard and may be considered a **Class I Cover Fabric**. There were no ignitions on any of the three specimens tested. In addition, none of the three test specimens displayed a vertical char which was equal to or greater than 45 mm.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Bobby E. Puett

BEP/mr
Attachment



DIVERSIFIED

TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

May 21, 2014

Burch Fabrics
4200 Brockton Dr SE
Grand Rapids, MI 49512

Reference: Laboratory Test Report
Lab Identification No. 10422
Invoice No. 41178 (Attached)

Dear Ms. Houser:

One (1) fabric sample, identified as **COVE- CRYPTON**, was received and tested in accordance with the UPHOLSTERED FURNITURE ACTION COUNCIL Fabric Classification Test Method--1990. The results are as follows:

Test Results
Vertical Char Lengths

16mm	14mm	14mm
------	------	------

Class

I

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Bobby E. Puett

BEP/mr
Attachment