

**DIVERSIFIED**  
TESTING LABORATORIES, INC.  
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET  
P.O. BOX 4004  
BURLINGTON, NORTH CAROLINA 27215  
PHONE (336) 227-7710 • FAX (336) 227-1175  
www.diversifiedtestinglabs.com

January 30, 2020

BURCH FABRICS  
4200 Brockton Dr SE  
Grand Rapids, MI 49512

Reference: Laboratory Test Report  
Lab Identification No. 39976  
Invoice No. 71177

To Whom it May Concern:

One (1) sample, identified as **ENDURANCE**, was received and tested in accordance with the California Technical Bulletin 117-2013, Section 1, Cover Fabric Test. The results are as follows:

Test Results

Vertical Char Lengths

8mm

9mm

8mm

The sample submitted **meets** the requirements of the above standard. There were no ignitions or smoldering after 45 minutes on any of the three specimens tested. In addition, none of the three test specimens displayed a char which was greater than 45 mm.


If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr





# DIVERSIFIED

TESTING LABORATORIES, INC.  
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET  
P.O. BOX 4004  
BURLINGTON, NORTH CAROLINA 27215  
PHONE (336) 227-7710 • FAX (336) 227-1175  
www.diversifiedtestinglabs.com

January 16, 2013

BURCH FABRICS  
4200 Brockton Drive SE  
Grand Rapids, MI 49512

Reference: Laboratory Test Report  
Lab Identification No. 4976  
Invoice No. 35678 (Attached)

To Whom it May Concern:

One (1) fabric sample, identified as **ENDURANCE**, was received and tested in accordance with the NFPA 260, "Cigarette Ignition Resistance of Components of Upholstered Furniture, 2009 Edition", (Cover Fabric Test). The results are as follows:

Test Results  
Vertical Char Lengths

11mm	13mm	12mm
------	------	------


The fabric sample submitted meets the requirements of the above standard and may be considered a **Class I Cover Fabric**. There were no ignitions on any of the three specimens tested. In addition, none of the three test specimens displayed a vertical char which was equal to or greater than 45 mm.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr  
Attachment



# DIVERSIFIED

TESTING LABORATORIES, INC.  
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET  
P.O. BOX 4004  
BURLINGTON, NORTH CAROLINA 27215  
PHONE (336) 227-7710 • FAX (336) 227-1175  
www.diversifiedtestinglabs.com

January 16, 2013

BURCH FABRICS  
4200 Brockton Drive SE  
Grand Rapids, MI 49512

Reference: Laboratory Test Report  
Lab Identification No. 4976  
Invoice No. 35678 (Attached)

To Whom it May Concern:

One (1) fabric sample, identified as **ENDURANCE**, was received and tested in accordance with the UPHOLSTERED FURNITURE ACTION COUNCIL Fabric Classification Test Method--1990. The results are as follows:

<u>Test Results</u>		
<u>Vertical Char Lengths</u>		
11mm	13mm	12mm
<u>Class</u>		
I		

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr  
Attachment