

Burch

TB Cal. 117-2013 Quality Assurance Lab Test Report

Test Date: 01/03/2022
Material #:
Material Name:
Customer ID: Engima EcoEase
Reference Material:
Contents: 58.91% POLY, 25.44% PCRPOLY, 15.65% NYLON
Wgt oz/Linear yd: 18.352

Section 1: Cover Fabric Test

	Length of Char in Inches
Specimen #1	0.875 Inch
Specimen #2	0.688 Inch
Specimen #3	0.688 Inch
Char Length:	Pass

If the char measures 1.8 inches or less, the result is passing.
If the char measures more than 1.8 inches, the result is failing.

**45 Minute Smolder
Resistance:** **Pass**

VP Product Assurance:	Jennifer Gwynn
Date:	05/05/2025
Telephone #:	828-874-2181

Burch

NFPA 260 Certificate Quality Assurance Lab Test Report

Test Date: 01/03/2022
Material #:
Material Name:
Customer ID: Engima EcoEase
Reference Material:
Contents: 58.91% POLY, 25.44% PCRPOLY, 15.65% NYLON
Wgt oz/Linear yd: 18.352

Section 1: Cover Fabric Test

	Length of Char in Inches
Specimen #1	0.875 Inch
Specimen #2	0.688 Inch
Specimen #3	0.688 Inch
Char Length:	Class I

If the char measures 1.75 inches or less, passing results are categorized as Class I. If the char measures more than 1.75 inches, the result is failing, Failing results are categorized as Class II

VP Product Assurance:	Jennifer Gwynn
Date:	05/05/2025
Telephone #:	828-874-2181

Burch

UFAC

Quality Assurance Lab Test Report

Test Date: 01/03/2022
Material #:
Material Name:
Customer ID: Engima EcoEase
Reference Material:
Contents: 58.91% POLY, 25.44% PCRPOLY, 15.65% NYLON
Wgt oz/Linear yd: 18.352

Section 1: Cover Fabric Test

	Length of Char in Inches
Specimen #1	0.875 Inch
Specimen #2	0.688 Inch
Specimen #3	0.688 Inch
Char Length:	Class I

If the char measures 1.75 inches or less, passing results are categorized as Class I. If the char measures more than 1.75 inches, the result is failing, Failing results are categorized as Class II

VP Product Assurance:	Jennifer Gwynn
Date:	05/05/2025
Telephone #:	828-874-2181