**DIVERSIFIED****TESTING LABORATORIES, INC.**
WORLDWIDE SERVICE336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

"We Test Per Your Request" →

December 14, 2012

**BURCH
FABRICS**Reference: Flammability Test Report
Lab Identification No. 4808
Invoice No. 35462 (Attached)

Dear Ms. Houser:

One (1) fabric sample, identified as **FELT** was received and tested in accordance with the NFPA 260, "Cigarette Ignition Resistance of Components of Upholstered Furniture, 2009 Edition", (Cover Fabric Test). The results are as follows:

Test Results
Vertical Char Lengths

13mm	12mm	12mm
------	------	------


The fabric sample submitted meets the requirements of the above standard and may be considered a **Class I Cover Fabric**. There were no ignitions on any of the three specimens tested. In addition, none of the three test specimens displayed a vertical char which was equal to or greater than 45 mm.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Bobby E. Puett

BEP/mr
Attachment

**DIVERSIFIED****TESTING LABORATORIES, INC.**
WORLDWIDE SERVICE336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

"We Test Per Your Request" →

December 14, 2012

**BURCH
FABRICS**Reference: Flammability Test Report
Lab Identification No. 4808
Invoice No. 35462 (Attached)

Dear Ms. Houser:

One (1) fabric sample, identified as **FELT** was received and tested in accordance with the UPHOLSTERED FURNITURE ACTION COUNCIL Fabric Classification Test Method--1990. The results are as follows:

Test Results
Vertical Char Lengths

13mm 12mm 12mm

Class

I

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Bobby E. Puett

BEP/mr
Attachment