

DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

MARCH 10, 2021

BURCH FABRICS
4200 Brockton Drive SE
Grand Rapids, MI 49512

Reference: Laboratory Test Report
Lab Identification No. 43996
Invoice No. 75227

To Whom it May Concern:

One (1) fabric sample, identified as **FLANNEL**, was received and tested in accordance with the California Technical Bulletin 117-2013, Section 1, Cover Fabric Test. The results are as follows:

Test Results

Char

8mm

9mm

8mm

The sample submitted **meets** the requirements of the above standard. There were no ignitions or smoldering after 45 minutes on any of the three specimens tested. In addition, none of the three test specimens displayed a char which was greater than 45 mm.


If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSDmr





DIVERSIFIED
TESTING LABORATORIES, INC.

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

January 28, 2011

BURCH FABRICS
4200 Brockton Dr SE
Grand Rapids, MI 49512

Reference: Laboratory Test Report

Lab Identification No. 6678
Invoice No. 28177 (Attached)

To Whom it May Concern:

One (1) fabric sample, identified as **STYLE: FLANNEL**, was received and tested in accordance with the NFPA 260, "Cigarette Ignition Resistance of Components of Upholstered Furniture, 2009 Edition", (Cover Fabric Test). The results are as follows:


<u>Test Results</u>		
<u>Vertical Char Lengths</u>		
15mm	13mm	15mm

The fabric sample submitted meets the requirements of the above standard and may be considered a **Class I Cover Fabric**. There were no ignitions on any of the three specimens tested. In addition, none of the three test specimens displayed a vertical char which was equal to or greater than 45 mm.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,


Karon S. Matkins



DIVERSIFIED
TESTING LABORATORIES, INC.

“We Test Per Your Request”

336 WEST FRONT STREET
 P.O. BOX 4004
 BURLINGTON, NORTH CAROLINA 27215
 PHONE (336) 227-7710 • FAX (336) 227-1175
 www.diversifiedtestinglabs.com

January 28, 2011

BURCH FABRICS
 4200 Brockton Dr SE
 Grand Rapids, MI 49512

Reference: Laboratory Test Report
 Lab Identification No. 6678
 Invoice No. 28177 (Attached)

To Whom it May Concern:

One (1) fabric sample, identified as **STYLE: FLANNEL**, was received and tested in accordance with the UPHOLSTERED FURNITURE ACTION COUNCIL Fabric Classification Test Method--1990. The results are as follows:

<u>Test Results</u>		
<u>Vertical Char Lengths</u>		
15mm	13mm	15mm
<u>Class</u>		
I		

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Karon S. Matkins

KSM/mr
 Attachment