DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

August 12, 2025

BURCH FABRICS
4200 Brockton Dr SE , Grand Rapids , MI , 495 12

Reference: Laboratory Test Report
Lab Identification No. 65238
Invoice No. 96556

Dear Ms. Barton:

One (1) sample, identified as Fletcher, was received and tested in accordance with the California Technical Bulletin 117-2013, Section 1, Cover Fabric Test. The results are as follows:

Test Results

Vertical Char Lengths		
8mm	8mm	8mm

The sample submitted **meets** the requirements of the above standard. There were no ignitions or smoldering after 45 minutes on any of the three specimens tested. In addition, none of the three test specimens displayed a char which was greater than 45 mm.

Sincerely,

Brian S. Dement

BSD/mr

DIVERSIFIED TESTING LABORATORIES, INC. SEAL 1975 NORTH CAROLINA

OUR LETTERS AND REPORTS ARE FOR THE EXCLUSIVE USE OF THE CLIENT TO WHOM THEY ARE ADDRESSED. ANY COMMUNICATION TO OTHERS OR THE USE OF OUR COMPANY NAME MUST RECEIVE PRIOR APPROVAL. OUR TEST RESULTS APPLY ONLY TO THE SAMPLE TESTED AND ARE NOT NECESSARILY INDICATIVE OF THE QUALITIES OF APPARENTLY IDENTICAL OR SIMILAR PRODUCTS. UNLESS OTHERWISE SPECIFIED, ALL COMPLIANCE STATEMENTS ARE SIMPLE ACCEPTANCE. SAMPLES NOT DESTROYED IN TESTING ARE RETAINED A MAXIMUM OF THIRTY DAYS. THE LETTERS, REPORTS OR NAME OF DIVERSIFIED TESTING LABORATORIES, INC. MAY NOT BE USED IN ADVERTISING TO THE GENERAL PUBLIC.

DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

August 12, 2025

BURCH FABRICS

4200 Brockton Dr SE, Grand
Rapids, MI, 495 12

Reference: Laboratory Test Report
Lab Identification No. 65238
Invoice No. 96556

Dear Ms. Barton:

One (1) sample, identified as Fletcher, was received and tested in accordance with the NFPA 260, "Cigarette Ignition Resistance of Components of Upholstered Furniture, 2024 Edition", (Cover Fabric Test). The results are as follows:

Test Results

Vertical Char Lengths		
15mm	12mm	10mm

*Date Tested: August 12, 2025
*Conditioned minimum of 4 hours @ 70±5°F and >65% RH

The sample submitted **meets** the requirements of the above standard and may be considered a **Class I Cover Fabric.** There were no ignitions on any of the three specimens tested. In addition, none of the three test specimens displayed a vertical char which was equal to or greater than 45 mm.

Sincerely,

Brian S. Dement

BSD/mr

OUR LETTERS AND REPORTS ARE FOR THE EXCLUSIVE USE OF THE CLIENT TO WHOM THEY ARE ADDRESSED. ANY COMMUNICATION TO OTHERS OR THE USE OF OUR COMPANY NAME MUST RECEIVE PRIOR APPROVAL. OUR TEST RESULTS APPLY ONLY TO THE SAMPLE TESTED AND ARE NOT NECESSARILY INDICATIVE OF THE QUALITIES OF APPARENTLY IDENTICAL OR SIMILAR PRODUCTS. UNLESS OTHERWISE SPECIFIED, ALL COMPLIANCE STATEMENTS ARE SIMPLE ACCEPTANCE. SAMPLES NOT DESTROYED IN TESTING ARE RETAINED A MAXIMUM OF THIRTY DAYS. THE LETTERS, REPORTS OR NAME OF DIVERSIFIED TESTING LABORATORIES, INC. MAY NOT BE USED IN ADVERTISING TO THE GENERAL PUBLIC.

DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

August 12, 2025

BURCH FABRICS

4200 Brockton Dr SE, Grand
Rapids, MI, 495 12

Reference: Laboratory Test Report
Lab Identification No. 65238
Invoice No. 96556

Dear Ms. Barton:

One (1) sample, identified as Fletcher was received and tested in accordance with the UPHOLSTERED FURNITURE ACTION COUNCIL Fabric Classification Test Method--1990. The results are as follows:

Test Results

Vertical Char Lengths		
8mm	9mm	8mm

The sample submitted **meets** the requirements of the above standard and is a **Class I Cover Fabric.** There were no ignitions on any of the three specimens tested. In addition, none of the three test specimens displayed a vertical char which was equal to or greater than 44 mm.

Sincerely,

Brian S. Dement

BSD/mr

OUR LETTERS AND REPORTS ARE FOR THE EXCLUSIVE USE OF THE CLIENT TO WHOM THEY ARE ADDRESSED. ANY COMMUNICATION TO OTHERS OR THE USE OF OUR COMPANY NAME MUST RECEIVE PRIOR APPROVAL. OUR TEST RESULTS APPLY ONLY TO THE SAMPLE TESTED AND ARE NOT NECESSARILY INDICATIVE OF THE QUALITIES OF APPARENTLY IDENTICAL OR SIMILAR PRODUCTS. UNLESS OTHERWISE SPECIFIED, ALL COMPLIANCE STATEMENTS ARE SIMPLE ACCEPTANCE. SAMPLES NOT DESTROYED IN TESTING ARE RETAINED A MAXIMUM OF THIRTY DAYS. THE LETTERS, REPORTS OR NAME OF DIVERSIFIED TESTING LABORATORIES, INC. MAY NOT BE USED IN ADVERTISING TO THE GENERAL PUBLIC.