

# TECHNICAL REPORT

Burch

4200 Brockton Dr SE  
Grand Rapids, MI 49512  
(616) 698-2800

Customer information:  
BURCH FABRICS

## SAMPLE(S) FOR TEST:

Our Ref: BRC 933533

Test Date : 30/01/2023

Test End Date : 02/02/2023

Date: 06/02/2023

One, Composite – Ref: GRAMERCY

*Note: The above descriptions are as supplied by the client and have not been verified by KETS International who can take no responsibility for the accuracy of the description.*

### Conditioning

Prior to testing: At least 72 hours in ambient indoor conditions, then at least 16 hours in an atmosphere having a temperature of 20±5°C and a relative humidity of 50±20%

At time of testing: Temperature of 15 to 30°C and a relative humidity of 20% to 70%

TEST	SAMPLE 1
FLAMMABILITY TEST (CIGARETTE) - BS 5852 :1979 Part 1 source 0	P
FLAMMABILITY TEST (CIGARETTE) - CAL 117-2013	P
FLAMMABILITY TEST (CIGARETTE) -NFPA 260 Cigarette	P
FLAMMABILITY TEST (CIGARETTE) - BS EN 1021-1: 2014	P

P = MEETS BUYER'S REQUIREMENT / F = DOES NOT MEET BUYER'S REQUIREMENT / NR = NO REQUIREMENT / SC=STILL CONTINUES / X=NOT PERFORMED / NA = NOT APPLICABLE/ LS : LACK OF SAMPLE



## TEST REPORT

Burch

This report (including any enclosures and attachments) are prepared for the exclusive use of the Customer(s) named in the report and solely for the purpose for which it is provided and on the basis of instructions and information and/or materials supplied by Kets's Customer. The test results relate only to the specific items tested and are not intended to be a recommendation for any particular course of action. Customer is responsible for acting as it sees fit on the basis of such results. Unless Kets provide express prior written consent, no part of this report should be reproduced, distributed or communicated to any third party, nor could it be used for PR activities. Kets do not accept any liability if this report is used for an alternative purpose from which it is intended, nor do Kets owe any duty of care to any third party in respect of this report. Except where explicitly agreed in writing, all work and services performed is governed by Kets Standard Terms and Conditions of Service which is available on request or can be obtained at <http://www.kets.com.tr/terms>. Testing reports without signature are not valid. The sample has been provided by the customer and the results apply to the sample as received. Sample information is supplied by the customer. Unless otherwise requested, this laboratory applies shared risk decision rule. Unless otherwise is specified, all Pass or Fail results are given without uncertainty considered. The reported uncertainty is based on a standard uncertainty multiplied by a coverage factor k=2, providing a level of confidence of approximately 95%. The uncertainty evaluation has been carried out in accordance with ISO/IEC 17025 and TÜRKAK accreditation requirements. Tests marked (\*) in this test report are not included in the TÜRKAK accreditation schedule for this laboratory. Kets accredited by TÜRKAK under registration number [AB-0716-T] for [TS EN ISO IEC 17025] as test laboratory. Turkish Accreditation Agency (TÜRKAK) is a signatory to the European co-operation for Accreditation (EA) Multilateral Agreement (MLA) and to the International Laboratory Accreditation Cooperation (ILAC) Mutual Recognition Arrangement (MRA) for the recognition of test reports.

Test Method	Result	Requirements
-------------	--------	--------------

### Flammability Test BS 5852 :1979 Part 1 source 0 Cigarette

#### Test Specification

Test Method: BS 5852-1: 1979 as modified by Schedule 4 Part 1 and Schedule 5 Part 1 of The Furniture and Furnishing (fire) (safety) Regulations 1988 (as amended)  
 Criterion of Ignition: Ignition Source 0: Calibrated Senior Service Cigarette

Flame Application Time: 20±1 seconds

#### Filling Specification

Filling type: Polyurethane foam  
 Size: 450 x 300 x 75 mm (back) & 450 x 150 x 75 mm (seat)  
 Density / Hardness: 20-22 kg/m<sup>3</sup> / Type B Hardness grade 130

#### Pre-treatment / Durability procedure

The sample was water soaked as clause 4 of BS 5651: 1978 as modified by The Furniture and Furnishings (fire) (safety) Regulations 1988 (as amended) then line dried.

Test Method	Pre Treatment	Flammability Performance Requirements	Result			
BS 5852: Part 1: 1979, Ignition source 0 (Cigarette)	Watersoaked as clause 4.2 to 4.5 of BS 5651:1978 as modified by The Furniture and Furnishings (fire) (safety) Regulations 1988 (as amended) then Line dried.	Compliance with Schedule 4 Part 1 (The cigarette test) of The Furniture and Furnishings (fire) (safety) Regulations 1988 (as amended).	PASS			
<b>Note:</b> Fabric was submitted for test rather than the upholstery composite so as suggested by The Guide to the Furniture Regulations the cover fabric was tested for cigarette resistance using standard polyurethane foam (non-modified) as this will give the furniture manufacturer a good indication of its likelihood to pass the cigarette test for the finished article.						
Cigarette Test	Specimen No	Cigarette Burning Time	Flaming	Progressive Smouldering	Covering Splitting	Result
	1	22 min 17 sec	N	N	Y	PASS
	2	25 min 22 sec	N	N	Y	PASS

Y: Yes N: No N/A: Not Applicable P: Pass F: Fail D: Depth L: Length W: Width

#### Conclusion:

The composite tested meets the requirements of Schedule 4 Part 1 of the Furniture and Furnishings (fire) (safety) Regulations 1988 (as amended). **PASS**



## TEST REPORT

Burch

Test Method	Result	Requirements
(*)Flammability test- Ignition source: smouldering cigarette CAL TB 117:2013		

Conditioning : At least 24 hours in an atmosphere having a temperature of  $21^{\circ} \pm 3^{\circ} \text{C}$  ( $70^{\circ} \pm 5^{\circ} \text{F}$ ) and less than 55% relative humidity

Remark: No = Was not observed

### Test Method

The apparatus and method of testing were those described in California Technical Bulletin 117-2013, Section 1, for measuring the tendency of upholstery cover fabrics to smolder and contribute to fire propagation, when subjected to a smoldering ignition source.

### Pass/Fail Criteria

Specimen No	Vertical Char length (Inches)	Mock-up specimen continues to smolder After 45 Minutes	Mock-up test specimen transitions to open flaming	Test Result
1-	0.5	No	No	Pass
2-	0.3	No	No	Pass
3-	0.6	No	No	Pass

**RESULTS :** Based on the above Results and Acceptance Criteria, the item tested is:

☒ Pass

☐ Fail





## TEST REPORT

# Burch

Test Method	Result	Requirements
-------------	--------	--------------

### Flammability Test

NFPA 260 Cigarette

#### Test Method:

**TEST PERFORMED:** NFPA 260 Standard Methods of Tests and Classification System for Cigarette Ignition Resistance of Components of Upholstered Furniture – 2019; Fabric Cover Test and UFAC Fabric Classification Test Method – 1990; Standard Test Methods for Cigarette Ignition Resistance of Components of Upholstered Furniture ASTM E 1353-16 – Cover Fabric Test

**Test Conditions:** 70 ±4°F, 65 ±5% Relative Humidity

#### ACCEPTANCE CRITERIA

1. If the test specimen has no ignition, or if no individual specimen yields a vertical char of 45 mm (1.75 in.; ASTM states 1.8 in.) or less, the fabric is classified a Class I cover fabric.
2. If the vertical char of the test specimen greater than 45 mm (1.75 in.; ASTM states 1.8 in), the fabric is classified a Class II cover fabric.
3. If an obvious ignition of the polyurethane substrate occurs on the test assembly, the fabric is classified a Class II cover fabric.

Specimen	Char Length (in)
1	0.3
2	0.5
3	0.6

**RESULTS** Based on the above Results and Acceptance Criteria, the item tested is:

☒ Class I

☐ Class II

**CERTIFICATION** I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

## END OF TEST REPORT ##



# TEST REPORT

## RESULTS

Burch

Test Method	Results	Requirements
-------------	---------	--------------

(\*)Flammability test- Ignition source: smouldering cigarette

BS EN 1021-1:2014

### Test Specification

Side Tested:	Face
--------------	------

### Filling Specification

Filling Type:	Polyurethane foam
Size:	450 x 300 x 75 mm (back) & 450x150x 75 mm (seat)
Density/Hardness:	20-22 kg/m <sup>3</sup> , Type B Hardness grade130

### Pre-treatment / Durability procedure

None

### Conditioning

Prior to testing:	At least 72 hours in ambient indoor conditions, then at least 24 hours in an atmosphere having a temperature of 23±2°C and a relative humidity of 50±5%
At time of testing:	Temperature of 10°C to 30°C and a relative humidity of 15% to 80% Air flow rate of less than 0,2 m/s

Test Method	Pre Treatment	Requirements	Result
BS EN 1021-1: 2014 (Smouldering Cigarette)	None	As BS EN 1021-1: 2014 (Smouldering Cigarette)	PASS

	Specimen 1	Specimen 2
Criterion of ignition		
Smouldering Criteria		
Unsafe escalating combustion (3.1a)	NO	NO
Test assembly consumed (3.1b)	NO	NO
Smoulders to extremities (3.1c)	NO	NO
Smoulders through thickness (3.1c)	NO	NO
Smoulders more than 1 hour (3.1d)	NO	NO
In final examination, presence of activesmouldering (3.1e)	NO	NO
Flaming criteria	NO	NO
Occurrence of flames (3.2)	NO	NO
Comments		
Flaming ceased	-	-
Glowing ceased	-	-
Smoke ceased	-	-
Result (Non Ignition / Smouldering Ignition / Flaming Ignition)	NI	NI

Y: Yes    N: No    NA: Not Applicable    P: Pass    F: Fail

