

ISO: 9001 Certified

TB Cal. 117-2013 Quality Assurance Lab Test Report

Test Date:

07/26/2021

Material #:

Material Name:

Customer ID:

Illusion

Reference Material:

Contents:

83.96% POLY, 16.04% PCRPOLY

Wgt oz/Linear yd:

17.792

Section 1: Cover Fabric Test

Length of Char in Inches

Specimen #1

0.500 Inch

Specimen #2

0.500 Inch

Specimen #3

0.500 Inch

Char Length:

Pass

If the char measures 1.8 inches or less, the result is passing. If the char measures more than 1.8 inches, the result is failing.

45 Minute Smolder Resistance:

Pass

QA Lab Manager: Barbara Grant

Date:

09/09/2021

Telephone #: 828-893-4382



ISO: 9001 Certified

NFPA 260 Certificate Quality Assurance Lab Test Report

Test Date:

07/26/2021

Material #:

Material Name:

Customer ID:

Illusion

Reference Material:

Contents:

83.96% POLY, 16.04% PCRPOLY

Wgt oz/Linear yd:

17.792

Section 1: Cover Fabric Test

Length of Char in Inches

Specimen #1

0.500 Inch

Specimen #2

0.500 Inch

Specimen #3

0.500 Inch

Char Length:

If the char measures 1.75 inches or less, passing results are categorizeed as Class I. If the char measures more than 1.75 inches, the result is failing, Failing results are categorized as Class II

QA Lab Manager:

Barbara Grant

Date:

09/09/2021

Telephone #:

828-893-4382



UFAC Quality Assurance Lab Test Report

Test Date:

07/26/2021

Material #:

Material Name:

Customer ID:

Illusion

Reference Material:

Contents:

83.96% POLY, 16.04% PCRPOLY

Wgt oz/Linear yd:

17.792

Section 1: Cover Fabric Test

Length of Char in Inches

Specimen #1

0.500 Inch

Specimen #2

0.500 Inch

Specimen #3

0.500 Inch

Char Length:

Class I

If the char measures 1.75 inches or less, passing results are categorizeed as Class I. If the char measures more than 1.75 inches, the result is failing, Failing results are categorized as Class II

QA Lab Manager:

Barbara Grant

Date:

09/09/2021

Telephone #:

828-893-4382