

**DIVERSIFIED**  
**TESTING LABORATORIES, INC.**  
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET  
P.O. BOX 4004  
BURLINGTON, NORTH CAROLINA 27215  
PHONE (336) 227-7710 • FAX (336) 227-1175  
www.diversifiedtestinglabs.com

January 13, 2021

BURCH FABRICS  
4200 Brockton Drive SE  
Grand Rapids, MI 49512

Reference: Laboratory Test Report  
Lab Identification No. 43996  
Invoice No. 75227

To Whom it May Concern:

One (1) fabric sample, identified as **MAZE**, was received and tested in accordance with the California Technical Bulletin 117-2013, Section 1, Cover Fabric Test. The results are as follows:

**Test Results**

Vertical Char Lengths

17mm

15mm

15mm

The sample submitted **meets** the requirements of the above standard. There were no ignitions or smoldering after 45 minutes on any of the three specimens tested. In addition, none of the three test specimens displayed a char which was greater than 45 mm.


If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSDmr





**DIVERSIFIED**  
**TESTING LABORATORIES, INC.**  
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET  
P.O. BOX 4004  
BURLINGTON, NORTH CAROLINA 27215  
PHONE (336) 227-7710 • FAX (336) 227-1175  
www.diversifiedtestinglabs.com

January 13, 2021

BURCH FABRICS  
4200 Brockton Drive SE  
Grand Rapids, MI 49512

Reference: Laboratory Test Report  
Lab Identification No. 43996  
Invoice No. 75227

To Whom it May Concern:

One (1) fabric sample, identified as **MAZE**, was received and tested in accordance with the UPHOLSTERED FURNITURE ACTION COUNCIL Fabric Classification Test Method--1990. The results are as follows:

**Test Results**

Vertical Char Lengths

15mm

15mm

14mm

The sample submitted **meets** the requirements of the above standard and is a **Class I Cover Fabric**. There were no ignitions on any of the three specimens tested. In addition, none of the three test specimens displayed a vertical char which was equal to or greater than 44 mm.


If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSDmr





**DIVERSIFIED**  
TESTING LABORATORIES, INC.  
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET  
P.O. BOX 4004  
BURLINGTON, NORTH CAROLINA 27215  
PHONE (336) 227-7710 • FAX (336) 227-1175  
www.diversifiedtestinglabs.com

January 13, 2021

BURCH FABRICS  
4200 Brockton Drive SE  
Grand Rapids, MI 49512

Reference: Laboratory Test Report  
Lab Identification No. 43996  
Invoice No. 75227

To Whom it May Concern:

One (1) fabric sample, identified as **MAZE**, was received and tested in accordance with the NFPA 260, “Cigarette Ignition Resistance of Components of Upholstered Furniture, 2019 Edition”, (Cover Fabric Test). The results are as follows:

**Test Results**

Vertical Char Lengths

15mm

15mm

14mm

The sample submitted **meets** the requirements of the above standard and may be considered a **Class I Cover Fabric**. There were no ignitions on any of the three specimens tested. In addition, none of the three test specimens displayed a vertical char which was equal to or greater than 45 mm.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSDmr

