

## CERTIFICATE OF TESTING

For the Account Of: **Burch Fabrics**  
4200 Brockton Dr SE  
Grand Rapids, MI 49512

Contact:

Client's Identification: **Fable, Footnote, Index, Journal, Memoir, and Script**

**TEST PERFORMED** California Technical Bulletin 117, Section E (CPSC 16 CFR 1610 – CS 191-53) Upholstery Fabrics, March 2000

### TEST RESULTS

☒ Plain Surface ☐ Raised Surface

Specimen	Flame Spread Warp Face (s)	Flame Spread Warp Back (s)
1	DNI	
2	DNI	
3	DNI	
4		DNI
5		DNI

Specimen	Flame Spread Fill Face (s)	Flame Spread Fill Back (s)
1	DNI	
2	DNI	
3	DNI	
4		DNI
5		DNI

### ABBREVIATIONS USED

DNI Did not ignite when exposed to test ignition source  
IBE Ignited but extinguished before burning through stop cord  
SF Surface flash only; stop cord not burned & no burning/charring/fusing of the base fabric  
TSF Timed surface flash; stop cord burned, but no burning/charring/fusing of the base fabric

### ACCEPTANCE CRITERIA

1. With nap Minimum flame spread of any individual specimens shall be 7 seconds. (ACT Criteria decreases minimum time to 4 seconds)
2. Without nap Minimum flame spread of any individual specimens shall be 3.5 seconds.

### CONCLUSION

Based on the above Results and Acceptance Criteria, the item tested:  
☒ Complies  
☐ Does Not Comply

**CERTIFICATION** I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

*C. VanHusen*

Authorized Signature-MB

## CERTIFICATE OF TESTING

For the Account Of: Burch  
4200 Brockton Dr SE  
Grand Rapids, MI 49512

Contact: Customer Service

Client's Identification: Memoir

**TEST PERFORMED** California Technical Bulletin 117: June 2013 – Requirements, Test Procedure and Apparatus for Testing the Smolder Resistance of Materials Used in Upholstered Furniture – Cover Fabric Test

### TEST RESULTS

Specimen	Char Length (in)	Extinguished in 45 minutes? (Y/N)
1	Self-Extinguished	Y
2	Self-Extinguished	Y
3	Self-Extinguished	Y

### NOTES

Test Conditions: 70 ±5°F, 50 ±5% Relative Humidity

### ACCEPTANCE CRITERIA

A material is considered to pass or fail based on the following criteria:

- A single mock-up test specimen fails to meet the requirements of this test procedure if any of the following criteria occurs:
  - The mock-up test specimen continues to smolder after the 45 minute test duration
  - A vertical char length of more than 1.8 inches (45mm) develops on the cover fabric
  - The mock-up test specimen transitions to open flaming
- The cover fabric passes the test if three initial mock-up specimens pass the test, i.e. the cigarettes burn their full length and are no longer smoldering
- If more than one initial specimen fails, the cover fabric fails the test
- If any one of the three initial specimens fails, repeat the test on additional three specimens
- If all three additional specimens pass the test, the cover fabric passes the test. If any one of the additional three specimens fails, the cover fabric fails the test


### CONCLUSION

Based on the above Results and Acceptance Criteria, the item tested is:

- ☒ Pass  
☐ Fail

**CERTIFICATION** I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Authorized Signature-MB





The  
**Govmark**  
Organization, Inc.

96-D Allen Boulevard  
Farmingdale, New York 11735-5826 USA  
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956  
e-mail: info@govmark.com

Page 1

Received: 12/13/2013		Completed: 12/17/2013		Letter: S	AM	P.O.#:	Test Report #:	2-99977-0-									
Client's Identification		Memoir															
Tested For:		<b>BURCH FABRICS</b>					Key Test: IMO MSC 88/26/Add.2 Part 8 (3.1) 215 Tel: 1-(212)-643-8080 Ext: 310 Fax: 1-(212)-643-2626										
Category: Uph. Furniture (cig)      Specifier: IMO      PC: 16H      /dl TEST PERFORMED: IMO 2010 FTP Code - International Code for Application of Fire Test Procedures - Resolution MSC.307(88): Annex I - Fire Test Procedures, Part 8 - Test For Upholstered Furniture IGNITION SOURCE: Smouldering cigarette (section 3.1) TEST ITEM COMPOSITE: Cover Fabric -- <input checked="" type="checkbox"/> Client's cover fabric: (see "Client's Identification" section above) <input type="checkbox"/> Standard cover fabric, 100% inherently flame retardant polyester fabric, approx. 220 g/m <sup>2</sup> Filling Material -- <input checked="" type="checkbox"/> Standard filling material, as listed below: <input checked="" type="checkbox"/> Non flame retardant flexible polyether foam, 22 kg/m <sup>3</sup> (1.4 lb/ft <sup>3</sup> ) <input type="checkbox"/> Flame retardant polyurethane foam, Code Red II 35, 45 kg/m <sup>3</sup> (2.8 lb/ft <sup>3</sup> ) <input type="checkbox"/> Non flame retardant flexible polyether foam, 22 kg/m <sup>3</sup> (1.4 lb/ft <sup>3</sup> ), wrapped with Uniguard fire blocking material <input type="checkbox"/> Client's filling material: WATER SOAKING: Is not mandated by MSC.307(88) RESULTS: <table style="margin-left: auto; margin-right: auto; border: none;"> <tr> <td></td> <td style="text-align: center;">Progressive Smouldering Within 1 hr After Start of Test (yes/no)</td> <td style="text-align: center;">Flaming Within 1 hr After Start of Test (yes/no)</td> </tr> <tr> <td>Initial Test:</td> <td style="text-align: center;">No</td> <td style="text-align: center;">No</td> </tr> <tr> <td>Retest:</td> <td style="text-align: center;">No</td> <td style="text-align: center;">No</td> </tr> </table>										Progressive Smouldering Within 1 hr After Start of Test (yes/no)	Flaming Within 1 hr After Start of Test (yes/no)	Initial Test:	No	No	Retest:	No	No
	Progressive Smouldering Within 1 hr After Start of Test (yes/no)	Flaming Within 1 hr After Start of Test (yes/no)															
Initial Test:	No	No															
Retest:	No	No															

(Page 1 of 2)


File Copy



The  
**Govmark**  
Organization, Inc.

96-D Allen Boulevard  
Farmingdale, New York 11735-5626 USA  
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956  
e-mail: info@govmark.com

Page 2

Received: 12/13/2013	Completed: 12/17/2013	Letter: S	AM	P.O.#:	Test Report #:	2-99977-0-
Client's Identification	Memoir					
Tested For:			<b>BURCH FABRICS</b>		Key Test: IMO MSC 88/26/Add.2 Part 8 (3.1) 215 Tel: 1-(212)-643-8080 Ext: 310 Fax: 1-(212)-643-2626	

REMARKS: None.



**FAILURE CRITERIA:**

Progressive smouldering or flaming within one hour after start of test.

**CONCLUSION:** Based on the above Results and Failure Criteria, the item tested:

[x] Passes; [ ] Fails

**CERTIFICATION:** I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by IMO Resolution MSC.307(88).

  
AUTHORIZED SIGNATURE  
THE GOVMARK ORGANIZATION, INC. / ec 

DEC 31 2013

**MS. PHYLLIS PETTIT**

{Page 2 of 2}






The

**Govmark**

Organization, Inc.

98-D Allen Boulevard  
Farmingdale, New York 11735-5628 USA  
Tel. +1 (631) 283-8944 Fax +1 (631) 293-8956  
e-mail: info@govmark.com

Page 1

Received: 12/16/2013	Completed: 01/08/2014	Letter: B	CT	P.O.#:	Test Report #:	3-00001-0-
Client's Identification	Memoir					
Tested For:	 <b>BURCH FABRICS</b>		Key Test: ASTM E 84 (BLDG)		995	
			Tel: 1-(212)-643-8080		Ext: 310	
			Fax: 1-(212)-643-2626			
 BLDG (IBC): LE 2012; R 06/12; V 6/12 PC: ME /jd ASTM E84: LE 2012; R 06/12; V 06/12  TEST PERFORMED: ASTM E 84 - Standard Test Method for Surface Burning Characteristics of Building Materials *  REFERENCE: Comparable to: UL 723 - Standard for Test for Surface Burning Characteristics of Building Materials  APPROXIMATE THICKNESS OF SPECIMEN (as measured by Govmark): 0.051"  PRODUCT CATEGORY:  <input type="checkbox"/> Textile Type Product <input checked="" type="checkbox"/> Vinyl Type Product <input type="checkbox"/> Other than Textile Type or Vinyl Type Product: _____  * Note: Textile or expanded vinyl wallcoverings classified by this procedure are limited to use in sprinklered areas in certain public occupancies. If textile or expanded vinyl wallcoverings are used in non-sprinklered areas, a room/corner fire test is mandated, such as NFPA 265 for textiles and NFPA 286 for expanded vinyls.  NFPA 286 test method standard applies not only to expanded vinyls, but also to all non-textile products. Therefore, it should be considered for all interior finish applications in non-sprinklered areas.  SPECIMEN MOUNTING:  <input type="checkbox"/> Self Supporting: The test specimen, the face of which was 23" ± 1" x 24", was such that it remained in position in the tunnel during the fire test, and no additional support was required.  <input type="checkbox"/> Adhered to IRC: The test specimen was bonded to three 1/4" IRC (Inorganic Reinforced Cement) boards (a cement asbestos substitute) to form a test specimen the face of which was 23" ± 1" x 24".  <input type="checkbox"/> Adhered to Gypsum: The test specimen was adhered to 5/8" thick Type X gypsum board, to form a test specimen the face of which was 23" ± 1" x 24".  <input checked="" type="checkbox"/> Unadhered: The 23" ± 1" x 24" specimen was not adhered to any substrate. Instead, it was laid over a 2" hexagonal wire mesh screen and 1/4" rods.  <input type="checkbox"/> Other: _____  (Page 1 of 2)						


File Copy



The  
**Govmark**  
Organization, Inc.

98-D Allen Boulevard  
Farmingdale, New York 11735-5826 USA  
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956  
e-mail: info@govmark.com

Page 2

Received: 12/16/2013	Completed: 01/08/2014	Letter: B	CT	P.O.#:	Test Report #:	3-00001-0-
Client's Identification:	Memoir					
Tested For:	 <b>BURCH FABRICS</b>				Key Test: ASTM E 84 (BLDG)	995
				Tel: 1-(212)-643-8080	Ext: 310	
				Fax: 1-(212)-643-2626		

REMARKS: None.

RESULTS:

Flame Spread Index: 5  
Smoke Developed: 90

CONCLUSION: Based on the above Results and Code Classification System the item tested is assigned a:

- ☒ Class I or A rating
- ☐ Class II or B rating
- ☐ Class III or C rating
- ☐ Fails to achieve a minimum classification thereby rendering the product unsuitable in terms of code requirement

DATA SUMMARY:

Time to Ignition: 00.17 minutes  
Maximum Flame Spread "Distance": 01.31 feet  
Maximum Flame Spread "Time": 00.52 minutes


CODE CLASSIFICATION SYSTEM:

	Flame Spread Index	Smoke Developed
Class I or A:	0 - 25	450 or less
Class II or B:	26 - 75	450 or less
Class III or C:	76 - 200	450 or less

BUILDING CODE CITATION FOR THE CLASSIFICATION SCHEME:

- (1) 2012 edition, NFPA 101 Life Safety Code, para. 10.2.3.4
- (2) 2012 edition, NFPA 5000 Building Construction & Safety Code, para. 10.3.2
- (3) 2012 edition, International Building Code, para. 803.1.1

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by ASTM E 84.

  
AUTHORIZED SIGNATURE  
THE GOVMARK ORGANIZATION, INC. CT / ec

Douglas W. Lipp

(Page 2 of 2)

JAN 10 2014



The  
**Govmark**  
Organization, Inc.

96-D Allen Boulevard  
Farmingdale, New York 11735-5626 USA  
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956  
e-mail: info@govmark.com

Page 1

Received: 12/13/2013	Completed: 12/17/2013	Letter: S	AM	P.O.#:	Test Report #:	2-99977-0-
Client's Identification	Style: Memoir 11/19/13. Finish: Ink Resistant. Color: Brown. End Use: Upholstery.					
Tested For: Burch 4200 Brockton Dr SE Grand Rapids, MI 49512		Key Test: IMO MSC 88/26/Add.2 Part 8 (3.1) 215 Tel: 1-(212)-643-8080 Ext: 310 Fax: 1-(212)-643-2626				
Category: Uph.Furniture(cig)		Specifier: IMO		PC: 16H		/dl
TEST PERFORMED: IMO 2010 FTP Code - International Code for Application of Fire Test Procedures - Resolution MSC.307(88): Annex I - Fire Test Procedures, Part 8 - Test For Upholstered Furniture						
IGNITION SOURCE: Smouldering cigarette (section 3.1)						
TEST ITEM COMPOSITE:						
Cover Fabric --						
<input checked="" type="checkbox"/> Client's cover fabric: (see "Client's Identification" section above)						
<input type="checkbox"/> Standard cover fabric, 100% inherently flame retardant polyester fabric, approx. 220 g/m <sup>2</sup>						
Filling Material --						
<input checked="" type="checkbox"/> Standard filling material, as listed below:						
<input checked="" type="checkbox"/> Non flame retardant flexible polyether foam, 22 kg/m <sup>3</sup> (1.4 lb/ft <sup>3</sup> )						
<input type="checkbox"/> Flame retardant polyurethane foam, Code Red II 35, 45 kg/m <sup>3</sup> (2.8 lb/ft <sup>3</sup> )						
<input type="checkbox"/> Non flame retardant flexible polyether foam, 22 kg/m <sup>3</sup> (1.4 lb/ft <sup>3</sup> ), wrapped with Uniguard fire blocking material						
<input type="checkbox"/> Client's filling material:						
WATER SOAKING: Is not mandated by MSC.307(88)						
RESULTS:						
	Progressive Smouldering Within 1 hr After Start of Test (yes/no)	Flaming Within 1 hr After Start of Test (yes/no)				
Initial Test:	No	No				
Retest:	No	No				
(Page 1 of 2)						

File Copy





The  
**Govmark**  
Organization, Inc.

96-D Allen Boulevard  
Farmingdale, New York 11735-5626 USA  
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956  
e-mail: info@govmark.com

Page 2

Received: 12/13/2013	Completed: 12/17/2013	Letter: S	AM	P.O.#:	Test Report #:	2-99977-0-
----------------------	-----------------------	-----------	----	--------	----------------	------------

Client's Identification	Style: Memoir 11/19/13. Finish: Ink Resistant. Color: Brown. End Use: Upholstery.
-------------------------	---

Tested For: Burch  
4200 Brockton Dr SE  
Grand Rapids, MI 49512

Key Test: IMO MSC 88/26/Add.2 Part 8 (3.1) 215

Tel: 1-(212)-643-8080 Ext: 310  
Fax: 1-(212)-643-2626

REMARKS: None.

**FAILURE CRITERIA:**

Progressive smouldering or flaming within one hour after start of test.

CONCLUSION: Based on the above Results and Failure Criteria, the item tested:

[x] Passes; [ ] Fails

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by IMO Resolution MSC.307(88).

  
AUTHORIZED SIGNATURE  
THE GOVMARK ORGANIZATION, INC. / ec

DEC 31 2013

MS. PHYLLIS PETTIT

{Page 2 of 2}





TEXTILE TESTING  
CERTIFIED BEAUTY



TESTING CERT. #3193.01

Report Number: 64050  
Date: 04-03-2014

## CERTIFICATE OF TESTING

For the Account Of:



**BURCH  
FABRICS**

Contact:

Client's Identification: **Memoir**

### TEST PERFORMED

NFPA 260 Standard Methods of Tests and Classification System for Cigarette Ignition Resistance of Components of Upholstered Furniture – 2013; Fabric Cover Test and UFAC Fabric Classification Test Method – 1990; Standard Test Methods for Cigarette Ignition Resistance of Components of Upholstered Furniture ASTM E1353-08a<sub>e1</sub> – Cover Fabric Test

### TEST RESULTS

Specimen	Char Length (in)
1	Self-Extinguished
2	Self-Extinguished
3	Self-Extinguished

### NOTES

Test Conditions: 70 ±2°F, 65 ±2% Relative Humidity

### ACCEPTANCE CRITERIA

1. If the test specimen has no ignition, or if no individual specimen yields a vertical char of 45 mm (1.75 in.; ASTM states 1.8 in.) or less, the fabric is classified a Class I cover fabric.
2. If the vertical char of the test specimen greater than 45 mm (1.75 in.; ASTM states 1.8 in.), the fabric is classified a Class II cover fabric.
3. If an obvious ignition of the polyurethane substrate occurs on the test assembly, the fabric is classified a Class II cover fabric.

### CONCLUSION

Based on the above Results and Acceptance Criteria, the item tested is:

- ☒ Class I  
☐ Class II

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

*C. VanTimmer*

Authorized Signature-

## CERTIFICATE OF TESTING

For the Account Of:



**BURCH  
FABRICS**

Contact:

Client's Identification: **Memoir**

### TEST PERFORMED

Federal Motor Vehicle Safety Standard (FMVSS) 302 – October 1991, Flammability of Interior Materials CMVSS 302 – 2007, 49 CFR 571.302, Flammability of Polymeric Interior Materials – Horizontal Test Method SAE J369-2013, Standard Test Method for Horizontal Burning Rate of Polymeric Materials Used in Occupant Compartments of Motor Vehicles ASTM D5132-11

### TEST RESULTS

	Specimen	Burning Time Beyond 38 mm (s)	Burn Distance Beyond 38 mm (mm)	Burn Rate (mm/min)	Code
Length	1	0.0	0.0	NA	SE
	2	0.0	0.0	NA	SE
	3	0.0	0.0	NA	SE
	4	0.0	0.0	NA	SE
	5	0.0	0.0	NA	SE
Width	6	0.0	0.0	NA	SE
	7	59.5	80.0	80.7	SE/(B)
	8	0.0	0.0	NA	SE
	9	0.0	0.0	NA	SE
	10	33.0	11.0	NA	SE/NBR

#### Specimen Tested:

☐ Standard

☒ Modified, 1 mm wire spaced at 25mm intervals across 51 mm width opening:

☐ Test item was less than 56 mm wide

☒ Specimen softens and bends at flaming end, which results in erratic burning

#### ABBREVIATIONS USED

**SE/(B)** Self-extinguishing with burn rate. Specimen ignites; Time of burning after passing 38 mm is greater than 60 seconds and 51 mm before extinguishing.

**DNI** Does not ignite. Specimen does not support combustion during or after ignition.

**SE/O** Self-Extinguishing. Specimen ignites but does not burn to the timing zone, which starts at 38 mm.

**SE/NBR** Self-Extinguishing/No burn rate. Specimen ignites; burning progresses to the 38 mm timing start line and extinguishes within 51 mm beyond the start line and 60 seconds.

**B** Specimen ignites. Burning progresses more than 51 mm beyond the 38 mm timing start line. Burn rate is calculated.

**RB** Material transmits a flame across either surface more than 51mm beyond the first scribed line at a rate too fast to measure accurately; therefore, no calculation is required.

#### NOTES

Test Conditions: 70 ±2°F, 65 ±2% Relative Humidity

Thickness of Material: .042

Type of Specimen Tested: Textile

Prior Treatment, if applicable: None

*Continued, page 2*

#### ACCEPTANCE CRITERIA

553 76<sup>th</sup> Street, Byron Center, MI 49315

P: 616-559-6123 E: [testlab@applied-textiles.com](mailto:testlab@applied-textiles.com)

Page 1 of 2



TEXTILE TESTING

CERTIFIED PLANT



TESTING CERT. #3193.01

Report Number: 64050

Date: 04-03-2014

## CERTIFICATE OF TESTING

1. Burn rate must not exceed 102 mm/min for any specimen

### CONCLUSION

Based on the above Results and Acceptance Criteria, the item tested:

- ☒ Passes  
☐ Fails

**CERTIFICATION** I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

*C. Venturini*

Authorized Signature-MB

**ASTM Note:** In this procedure, the specimens are subjected to one or more specific laboratory test conditions. If different test conditions are substituted or the end-use conditions are changed, it is not always possible by or from this test to predict changes in the fire-test-response characteristics measured. Therefore, the results are valid only for the fire test exposure conditions described in this procedure.

**SAE Note:** This report is not intended to reflect hazards presented by this or any other material under actual fire conditions and shall not be used for fire risk assessment under actual fire conditions.





TEXTILE TESTING

OF BLUE ISLAND BLAUNT



TESTING CERT. #3193.01

Report Number: 64050

Date: 04-03-2014

## CERTIFICATE OF TESTING

For the Account Of: Burch Fabrics  
4200 Brockton Dr SE  
Grand Rapids, MI 49512

Contact:

Client's Identification: Fable, Footnote, Index, Journal, Memoir, and Script

**TEST PERFORMED** NFPA 260 Standard Methods of Tests and Classification System for Cigarette Ignition Resistance of Components of Upholstered Furniture – 2013; Fabric Cover Test and UFAC Fabric Classification Test Method – 1990; Standard Test Methods for Cigarette Ignition Resistance of Components of Upholstered Furniture ASTM E1353-08ae1 – Cover Fabric Test

### TEST RESULTS

Specimen	Char Length (in)
1	Self-Extinguished
2	Self-Extinguished
3	Self-Extinguished

### NOTES

Test Conditions: 70  $\pm$ 2°F, 65  $\pm$ 2% Relative Humidity

### ACCEPTANCE CRITERIA

1. If the test specimen has no ignition, or if no individual specimen yields a vertical char of 45 mm (1.75 in.; ASTM states 1.8 in.) or less, the fabric is classified a Class I cover fabric.
2. If the vertical char of the test specimen greater than 45 mm (1.75 in.; ASTM states 1.8 in.), the fabric is classified a Class II cover fabric.
3. If an obvious ignition of the polyurethane substrate occurs on the test assembly, the fabric is classified a Class II cover fabric.

### CONCLUSION

Based on the above Results and Acceptance Criteria, the item tested is:

- ☒ Class I  
☐ Class II

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

*C. VanHusen*

Authorized Signature-