ISO: 9001 Certified

UFAC Quality Assurance Lab Test Report

Date: 01/08/2019

Material #:

Material Name: Mercer

Reference Material:

Contents: 100.00% OLEFIN

Wgt oz/Linear yd: 17.6

Section 1: Cover Fabric Test

Length of Char in Inches

Specimen #1 0.500 Inch Specimen #2 0.500 Inch Specimen #3 0.500 Inch Char Length: Class I

If the char measures 1.75 inches or less, passing results are categorizeed as Class I. If the char measures more than 1.75 inches, the result is failing, Failing results are categorized as Class II

QA Lab Manager: Barbara Grant

01/08/2019 Date:

828-893-4382 Telephone #:

ISO: 9001 Certified

NFPA 260 Certificate Quality Assurance Lab Test Report

Date: 01/08/2019

Material #:

Material Name: Mercer

Reference Material:

Contents: 100.00% OLEFIN

Wgt oz/Linear yd: 17.6

Section 1: Cover Fabric Test

Length of Char in Inches

Specimen #1 0.500 Inch Specimen #2 0.500 Inch 0.500 Inch Specimen #3 Class I Char Length:

If the char measures 1.75 inches or less, passing results are categorizeed as Class I. If the char measures more than 1.75 inches, the result is failing, Failing results are categorized as Class II

QA Lab Manager: Barbara Grant

01/08/2019 Date:

828-893-4382 Telephone #:

ISO: 9001 Certified

TB Cal. 117-2013 Quality Assurance Lab Test Report

Date:

01/08/2019

Material #:

Material Name:

Mercer

Reference Material:

Contents:

100.00% OLEFIN

Wgt oz/Linear yd:

17.6

Section 1: Cover Fabric Test

Length of Char in Inches

Specimen #1

0.500 Inch

Specimen #2

0.500 Inch

Specimen #3

0.500 Inch

Char Length:

Pass

If the char measures 1.8 inches or less, the result is passing. If the char measures more than 1.8 inches, the result is failing.

45 Minute Smolder Resistance:

Pass

QA Lab Manager:

Barbara Grant

Date:

01/08/2019

Telephone #:

828-893-4382