



CAL 117 Section E, Part I – Upholstery Fabrics

Date RECEIVED APR 20 2011

Customer Burch Fabrics

Pattern Neutra

Warp	1	2	3	4	5
Flame Spread with Nap (seconds)					
Flame Spread without Nap (seconds)	DNI	DNI	DNI	DNI	DNI

Fill	1	2	3	4	5
Flame Spread with Nap (seconds)					
Flame Spread without Nap (seconds)	DNI	DNI	DNI	DNI	DNI

Requirements:

With Nap – Minimum flame spread of any individual specimens shall not be less than 7 seconds.

Without Nap – Minimum flame spread of any individual specimens shall not be less than 3.5 seconds.

Conclusion:

The above results indicate Class 1 with the stated requirements.

I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by California Technical Bulletin 117, Section E, part I Upholstered Fabrics dated January 1980.

Bene Mitchell
QA Lab Manager

RECEIVED APR 20 2011
Date



UFAC
Quality Assurance Lab Test Report

Date RECEIVED APR 20 2011

Customer Burch Fabrics

Pattern Neutra

Length of char in inches

Specimen # 1 .045 Class 1

Specimen # 2 .045 Class 1

Specimen # 3 .045 Class 1

If the char measures 1.75 inches or less, the result is passing. Passing results are categorized as Class 1.

If the char measures more than 1.75 inches, the result is failing. Failing results are categorized as Class 2.

Rexie Michel
QA Lab Manager

RECEIVED APR 20 2011
Date