

Fabric Testing Laboratory

Pattern Tested: Nimbus

Date: 7/29/2017

Tested For: Burch

Test Performed: Cal TB 117-2013

NFPA 260/UFAC 1 Based on Cal 117-2013 Results

Cigarette Ignition Resistance of Fabric Intended for Use in Upholstered Furniture

RESULTS:

| Specimen | Ignition (Yes/No/SE) | Char Length On Vertical Panel (inches) |
|----------|-------------------------|---|
| #1 | DNI | 0.88 |
| #2 | DNI | 0.88 |
| #3 | DNI | 0.75 |

SE - Indicates that the cigarette self extinguished prior to burning its entire length. When this occurs, a "retest" of that specimen is performed

Remarks: NONE

Classification System:

- Class 1 - For each specimen: No obvious ignition; char length less than 1.75"
(Indicates propensity to resist cigarette ignition in conjunction with standard foam filling material.)
- Class 2 - For any specimen: Obvious ignition or char length 1.75" or greater
(Indicates inability to resist cigarette ignition with standard foam filling materials)

Conclusion: Based on the above results and acceptance criteria, the item tested is assigned a:

(XX) Class 1 Rating
() Class 2 Rating

Certification: I certify that the above results were the result of testing on the construction listed above in accordance with the testing procedures and equipment specified by Cal TB 117-2013

David Ryan
Authorized Signature
Wearbest Sil-Tex Mills, Ltd.